

TRIPET® 2550GN15

Samyang Corporation - Polyethylene Terephthalate

General Information

Product Description

TRIPET® has excellent mechanical properties and dimensional stability, and good electrical property, widely used in the field of automobile, electric & electronics.

General

Material Status	• Commercial: Active
Availability	• Asia Pacific • Europe • North America
Uses	• General Purpose
Forms	• Pellets

 Properties ¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	1.51		ASTM D792
Melt Mass-Flow Rate (MFR) (265°C/5.0 kg)	42	g/10 min	ASTM D1238
Molding Shrinkage - Flow	2.0E-3 to 4.0E-3	in/in	ASTM D955
Water Absorption (24 hr, 73°F)	< 0.10	%	ASTM D570
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	15600	psi	ASTM D638
Tensile Elongation (Break)	3.0	%	ASTM D638
Flexural Modulus	925000	psi	ASTM D790
Flexural Strength (Yield)	21300	psi	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (73°F, 0.125 in)	1.7	ft·lb/in	ASTM D256
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	114		ASTM D785
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (66 psi, Unannealed)	464	°F	ASTM D648
Deflection Temperature Under Load (264 psi, Unannealed)	428	°F	ASTM D648
CLTE - Flow	1.7E-5	in/in/°F	ASTM D696
RTI Elec (0.12 in)	284	°F	UL 746B
RTI Imp (0.12 in)	284	°F	UL 746B
RTI Str (0.12 in)	284	°F	UL 746B
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	1.0E+16	ohms·cm	ASTM D257
Dielectric Strength	510	V/mil	ASTM D149
Dielectric Constant	3.80		ASTM D150
Dissipation Factor	0.017		ASTM D150
Arc Resistance	80.0	sec	ASTM D495
Flammability	Nominal Value	Unit	Test Method
Flame Rating (0.030 in)	V-0		UL 94

