

**DELTRIN 500P BK602**

Delrin USA, LLC - Acetal (POM) Homopolymer

**General Information**
**General**

Material Status	• Commercial: Active		
Availability	• Africa & Middle East	• Europe	• North America
	• Asia Pacific	• Latin America	
Additive	• Mold Release		
Features	• General Purpose	• Good Processability	• Homopolymer
	• Good Mold Release	• Good Thermal Stability	• Medium Viscosity
Uses	• General Purpose		
RoHS Compliance	• Contact Manufacturer		
Automotive Specifications	• FORD WSK-M4D637-A2	• GM QK 000326 Type B	• STELLANTIS MS-DB-100
	• GM GMP.POM.002	• IMDS ID 14150625 Color: BK602 Black	• CPN2206
ISO Designation (ISO 29988)	• POM-H,,MACR,4-2		
Part Marking Code (ISO 11469)	• >POM<		
Resin ID (ISO 1043)	• POM		

**Properties <sup>1</sup>**

Physical	Nominal Value	Unit	Test Method
Density	1.42	g/cm <sup>3</sup>	ISO 1183
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	15	g/10 min	ISO 1133
Melt Volume-Flow Rate (MVR) (190°C/2.16 kg)	13	cm <sup>3</sup> /10min	ISO 1133
Molding Shrinkage			ISO 294-4
Across Flow	1.8	%	
Flow	2.0	%	
Water Absorption (Saturation, 73°F, 0.0787 in)	1.3	%	ISO 62
Water Absorption (Equilibrium, 73°F, 0.0787 in, 50% RH)	0.40	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	450000	psi	ISO 527-1
Tensile Stress (Yield)	10300	psi	ISO 527-2
Tensile Strain (Yield)	14	%	ISO 527-2
Nominal Tensile Strain at Break	25	%	ISO 527-2
Flexural Modulus	435000	psi	ISO 178
Poisson's Ratio	0.37		
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			ISO 179/1eA
-22°F	3.3	ft·lb/in <sup>2</sup>	
73°F	3.8	ft·lb/in <sup>2</sup>	
Charpy Unnotched Impact Strength			ISO 179/1eU
-22°F	76	ft·lb/in <sup>2</sup>	
73°F	95	ft·lb/in <sup>2</sup>	
Notched Izod Impact Strength			ISO 180/1A
-40°F	3.8	ft·lb/in <sup>2</sup>	
73°F	3.8	ft·lb/in <sup>2</sup>	
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (66 psi, Unannealed)	324	°F	ISO 75-2/B
Deflection Temperature Under Load (264 psi, Unannealed)	205	°F	ISO 75-2/A
Melting Temperature <sup>2</sup>	352	°F	ISO 11357-3



CLTE - Flow		ISO 11359-2
--	5.6E-5 in/in/°F	
-40 to 73°F	5.0E-5 in/in/°F	
CLTE - Transverse		ISO 11359-2
--	5.6E-5 in/in/°F	
-40 to 73°F	5.0E-5 in/in/°F	
RTI Elec		UL 746B
0.030 in	122 °F	
0.06 in	230 °F	
0.12 in	230 °F	
RTI Imp		UL 746B
0.030 in	122 °F	
0.06 in	185 °F	
0.12 in	194 °F	
RTI Str		UL 746B
0.030 in	122 °F	
0.06 in	194 °F	
0.12 in	203 °F	
Annealing Temperature	320 °F	
Annealing Time - Optional	30.0 min/mm	

Electrical	Nominal Value	Unit	Test Method
Comparative Tracking Index	600	V	IEC 60112

Flammability	Nominal Value	Unit	Test Method
Burning Rate <sup>3</sup> (0.0394 in)	1.7	in/min	ISO 3795
Flame Rating			UL 94
0.031 in		HB	
0.06 in		HB	
Flammability Classification			IEC 60695-11-10, -20
0.03 in		HB	
0.06 in		HB	

FMVSS Flammability	B		FMVSS 302
--------------------	---	--	-----------

Additional Information	Nominal Value	Unit	Test Method
Emission	< 8	ppm	VDA 275
Fogging			ISO 6452
F-value (refraction)	90	%	
G-value (condensate)	0.35	mg	

### Processing Information

Injection	Nominal Value	Unit
Drying Temperature	176	°F
Drying Time - Desiccant Dryer	2.0 to 4.0	hr
Suggested Max Moisture	< 0.20	%
Processing (Melt) Temp	410 to 428	°F
Melt Temperature, Optimum	419	°F
Mold Temperature	176 to 212	°F
Mold Temperature, Optimum	194	°F
Holding Pressure	11600 to 14500	psi
Drying Recommended	yes	
Hold Pressure Time	8.00	s/mm

### Notes

<sup>1</sup> Typical properties: these are not to be construed as specifications.

<sup>2</sup> 10°C/min

<sup>3</sup> FMVSS 302

