

DELTRIN 100TE NC010

Delrin USA, LLC - Acetal (POM) Homopolymer

General Information
General

Material Status	<ul style="list-style-type: none"> Commercial: Active
Availability	<ul style="list-style-type: none"> Africa & Middle East Asia Pacific Europe Latin America North America
Additive	<ul style="list-style-type: none"> Impact Modifier Mold Release
Features	<ul style="list-style-type: none"> Good Mold Release High Viscosity Homopolymer Impact Modified Low VOC
Uses	<ul style="list-style-type: none"> Automotive Applications
RoHS Compliance	<ul style="list-style-type: none"> Contact Manufacturer
Part Marking Code (ISO 11469)	<ul style="list-style-type: none"> >POM-I<
Resin ID (ISO 1043)	<ul style="list-style-type: none"> POM-I

Properties ¹

Physical	Nominal Value	Unit	Test Method
Density	1.37	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	2.2	g/10 min	ISO 1133
Melt Volume-Flow Rate (MVR) (190°C/2.16 kg)	2.0	cm ³ /10min	ISO 1133
Molding Shrinkage			ISO 294-4
Across Flow	1.5	%	
Flow	1.3	%	
Water Absorption (Saturation, 73°F, 0.0787 in)	0.80	%	ISO 62
Water Absorption (Equilibrium, 73°F, 0.0787 in, 50% RH)	0.30	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	268000	psi	ISO 527-1
Tensile Stress (Yield)	7830	psi	ISO 527-2
Tensile Strain (Yield)	26	%	ISO 527-2
Nominal Tensile Strain at Break	> 50	%	ISO 527-2
Flexural Stress (3.5% Strain)	7400	psi	ISO 178
Poisson's Ratio	0.41		
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			ISO 179/1eA
-22°F	6.2	ft-lb/in ²	
73°F	11	ft-lb/in ²	
Charpy Unnotched Impact Strength			ISO 179/1eU
-22°F	No Break		
73°F	No Break		
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness			ISO 2039-2
M-Scale	65		
R-Scale	113		
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (66 psi, Unannealed)	259	°F	ISO 75-2/B
Deflection Temperature Under Load (264 psi, Unannealed)	160	°F	ISO 75-2/A
Vicat Softening Temperature	343	°F	ISO 306/A50
Melting Temperature ²	352	°F	ISO 11357-3
CLTE - Flow	6.7E-5	in/in/°F	ISO 11359-2
CLTE - Transverse	6.7E-5	in/in/°F	ISO 11359-2



Annealing Temperature	320 °F		
Annealing Time - Optional	30.0 min/mm		
Flammability	Nominal Value	Unit	Test Method
Burning Rate ³ (0.0394 in)	2.3 in/min		ISO 3795
FMVSS Flammability	B		FMVSS 302
Fill Analysis	Nominal Value	Unit	Test Method
Melt Density	1.16 g/cm ³		
Additional Information	Nominal Value	Unit	Test Method
Emission	< 2 ppm		VDA 275

Processing Information

Injection	Nominal Value	Unit
Drying Temperature	176 °F	
Drying Time - Desiccant Dryer	4.0 to 8.0 hr	
Suggested Max Moisture	< 0.050 %	
Processing (Melt) Temp	392 to 410 °F	
Melt Temperature, Optimum	401 °F	
Mold Temperature	104 to 140 °F	
Mold Temperature, Optimum	122 °F	
Holding Pressure	8700 to 11600 psi	
Drying Recommended	yes	
Hold Pressure Time	7.50 s/mm	
Maximum Screw Tangential Speed	472 in/min	
Extrusion	Nominal Value	Unit
Drying Temperature	167 to 185 °F	
Drying Time	2.0 to 4.0 hr	
Suggested Max Moisture	< 0.050 %	
Melt Temperature	383 to 401 °F	
Extrusion Melt Temperature, Optimum	392 °F	

Notes

¹ Typical properties: these are not to be construed as specifications.

² 10°C/min

³ FMVSS 302

