

DELTRIN 900P BK602

Delrin USA, LLC - Acetal (POM) Homopolymer

General Information

General			
Material Status	• Commercial: Active		
Availability	• Africa & Middle East • Asia Pacific	• Europe • Latin America	• North America
Additive	• Mold Release		
Features	• General Purpose • Good Mold Release	• Good Processability • Good Thermal Stability	• Homopolymer • Low Viscosity
Uses	• General Purpose		
RoHS Compliance	• Contact Manufacturer		
Automotive Specifications	• FORD WSK-M4D637-A3	• GM GMP.POM.009	• STELLANTIS MS-DB-100 CPN4043
Part Marking Code (ISO 11469)	• >POM<		
Resin ID (ISO 1043)	• POM		

Properties ¹

Physical	Nominal Value	Unit	Test Method
Density	1.42	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	25	g/10 min	ISO 1133
Molding Shrinkage			ISO 294-4
Across Flow	1.7	%	
Flow	1.8	%	
Water Absorption (Equilibrium, 73°F, 0.0787 in, 50% RH)	0.40	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	479000	psi	ISO 527-1
Tensile Stress (Yield)	10200	psi	ISO 527-2
Tensile Strain (Yield)	12	%	ISO 527-2
Nominal Tensile Strain at Break	17	%	ISO 527-2
Flexural Modulus	435000	psi	ISO 178
Poisson's Ratio	0.37		
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			ISO 179/1eA
-22°F	2.9	ft·lb/in ²	
73°F	3.3	ft·lb/in ²	
Charpy Unnotched Impact Strength (73°F)	62	ft·lb/in ²	ISO 179/1eU
Notched Izod Impact Strength			ISO 180/1A
-40°F	3.3	ft·lb/in ²	
73°F	3.3	ft·lb/in ²	
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (66 psi, Unannealed)	322	°F	ISO 75-2/B
Deflection Temperature Under Load (264 psi, Unannealed)	208	°F	ISO 75-2/A
Melting Temperature ²	352	°F	ISO 11357-3
CLTE - Flow	5.6E-5	in/in/°F	ISO 11359-2
CLTE - Transverse			ISO 11359-2
--	5.6E-5	in/in/°F	
-40 to 73°F	5.0E-5	in/in/°F	
RTI Elec			UL 746B
0.030 in	122	°F	



0.06 in	230 °F	
0.12 in	230 °F	
RTI Imp		UL 746B
0.030 in	122 °F	
0.06 in	185 °F	
0.12 in	194 °F	
RTI Str		UL 746B
0.030 in	122 °F	
0.06 in	194 °F	
0.12 in	203 °F	
Annealing Temperature	320 °F	
Annealing Time - Optional	30.0 min/mm	

Flammability	Nominal Value	Unit	Test Method
Burning Rate ³ (0.0394 in)	0.63	in/min	ISO 3795
Flame Rating			UL 94
0.031 in	HB		
0.06 in	HB		
Flammability Classification			IEC 60695-11-10, -20
0.03 in	HB		
0.06 in	HB		
Oxygen Index	23	%	ISO 4589-2
FMVSS Flammability	B		FMVSS 302

Additional Information	Nominal Value	Unit	Test Method
Emission	< 8	ppm	VDA 275
Fogging			ISO 6452
F-value (refraction)	95	%	
G-value (condensate)	0.20	mg	

Processing Information

Injection	Nominal Value	Unit
Drying Temperature	176	°F
Drying Time - Desiccant Dryer	2.0 to 4.0	hr
Suggested Max Moisture	< 0.20	%
Processing (Melt) Temp	410 to 428	°F
Melt Temperature, Optimum	419	°F
Mold Temperature	176 to 212	°F
Mold Temperature, Optimum	194	°F
Holding Pressure	11600 to 14500	psi
Drying Recommended	yes	
Hold Pressure Time	8.00	s/mm

Notes

¹ Typical properties: these are not to be construed as specifications.

² 10°C/min

³ FMVSS 302

