

DELTRIN FG500P NC010

Delrin USA, LLC - Acetal (POM) Homopolymer

General Information

General			
Material Status	<ul style="list-style-type: none"> Commercial: Active 		
Availability	<ul style="list-style-type: none"> Africa & Middle East Asia Pacific 	<ul style="list-style-type: none"> Europe Latin America 	<ul style="list-style-type: none"> North America
Additive	<ul style="list-style-type: none"> Mold Release 		
Features	<ul style="list-style-type: none"> General Purpose Good Mold Release 	<ul style="list-style-type: none"> Good Processability Good Thermal Stability 	<ul style="list-style-type: none"> Homopolymer Medium Viscosity
RoHS Compliance	<ul style="list-style-type: none"> Contact Manufacturer 		
Part Marking Code (ISO 11469)	<ul style="list-style-type: none"> >POM< 		
Resin ID (ISO 1043)	<ul style="list-style-type: none"> POM 		

Properties ¹

Physical	Nominal Value	Unit	Test Method
Density	1.42	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	15	g/10 min	ISO 1133
Melt Volume-Flow Rate (MVR) (190°C/2.16 kg)	13	cm ³ /10min	ISO 1133
Molding Shrinkage			ISO 294-4
Across Flow	1.9	%	
Flow	2.0	%	
Water Absorption (Saturation, 73°F, 0.0787 in)	1.4	%	ISO 62
Water Absorption (Equilibrium, 73°F, 0.0787 in, 50% RH)	0.40	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	450000	psi	ISO 527-1
Tensile Stress (Yield)	10300	psi	ISO 527-2
Tensile Strain (Yield)	17	%	ISO 527-2
Nominal Tensile Strain at Break	30	%	ISO 527-2
Tensile Creep Modulus (1 hr)	406000	psi	ISO 899-1
Tensile Creep Modulus (1000 hr)	232000	psi	ISO 899-1
Flexural Modulus	421000	psi	ISO 178
Flexural Stress (3.5% Strain)	11600	psi	ISO 178
Poisson's Ratio	0.37		
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			ISO 179/1eA
-40°F	3.8	ft·lb/in ²	
-22°F	3.8	ft·lb/in ²	
73°F	4.3	ft·lb/in ²	
Charpy Unnotched Impact Strength			ISO 179/1eU
-22°F	130	ft·lb/in ²	
73°F	140	ft·lb/in ²	
Notched Izod Impact Strength			ISO 180/1A
-22°F	3.8	ft·lb/in ²	
73°F	4.3	ft·lb/in ²	
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness			ISO 2039-2
M-Scale	92		
R-Scale	120		
Thermal	Nominal Value	Unit	Test Method



Deflection Temperature Under Load (66 psi, Unannealed)	316 °F	ISO 75-2/B
Deflection Temperature Under Load (264 psi, Unannealed)	199 °F	ISO 75-2/A
Vicat Softening Temperature	311 °F	ISO 306/B50
Melting Temperature ²	352 °F	ISO 11357-3
CLTE - Flow	6.1E-5 in/in/°F	ISO 11359-2
CLTE - Transverse	6.1E-5 in/in/°F	ISO 11359-2
RTI Elec		UL 746B
0.030 in	122 °F	
0.06 in	230 °F	
0.12 in	230 °F	
RTI Imp		UL 746B
0.030 in	122 °F	
0.06 in	185 °F	
0.12 in	194 °F	
RTI Str		UL 746B
0.030 in	122 °F	
0.06 in	194 °F	
0.12 in	203 °F	

Flammability	Nominal Value	Unit	Test Method
Flame Rating			UL 94
0.030 in		HB	
0.06 in		HB	
Flammability Classification			IEC 60695-11-10, -20
0.030 in		HB	
0.06 in		HB	

Additional Information	Nominal Value	Unit	Test Method
Emission	< 8	ppm	VDA 275
Emission of Organic Compounds	3.10	µgC/g	VDA 277
Fogging			ISO 6452
F-value (refraction)	90	%	
G-value (condensate)	0.35	mg	

Processing Information

Injection	Nominal Value	Unit
Drying Temperature	176	°F
Drying Time - Desiccant Dryer	2.0 to 4.0	hr
Suggested Max Moisture	< 0.20	%
Processing (Melt) Temp	410 to 428	°F
Melt Temperature, Optimum	419	°F
Mold Temperature	176 to 212	°F
Mold Temperature, Optimum	194	°F
Holding Pressure	11600 to 14500	psi
Drying Recommended	yes	
Hold Pressure Time	8.00	s/mm
Maximum Screw Tangential Speed	709	in/min

Notes

¹ Typical properties: these are not to be construed as specifications.

² 10°C/min

