

**DELTRIN FG900P NC010**

Delrin USA, LLC - Acetal (POM) Homopolymer

**General Information**

General			
Material Status	• Commercial: Active		
Availability	• Africa & Middle East • Asia Pacific	• Europe • Latin America	• North America
Additive	• Mold Release		
Features	• General Purpose • Good Mold Release	• Good Processability • Good Thermal Stability	• Homopolymer • Low Viscosity
Uses	• General Purpose		
RoHS Compliance	• Contact Manufacturer		
Part Marking Code (ISO 11469)	• >POM<		
Resin ID (ISO 1043)	• POM		

**Properties <sup>1</sup>**

Physical	Nominal Value	Unit	Test Method
Density	1.42	g/cm <sup>3</sup>	ISO 1183
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	25	g/10 min	ISO 1133
Melt Volume-Flow Rate (MVR) (190°C/2.16 kg)	21	cm <sup>3</sup> /10min	ISO 1133
Molding Shrinkage			ISO 294-4
Across Flow	1.9	%	
Flow	1.9	%	
Water Absorption (Saturation, 73°F, 0.0787 in)	1.4	%	ISO 62
Water Absorption (Equilibrium, 73°F, 0.0787 in, 50% RH)	0.40	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	479000	psi	ISO 527-1
Tensile Stress (Yield)	10300	psi	ISO 527-2
Tensile Strain (Yield)	12	%	ISO 527-2
Nominal Tensile Strain at Break	23	%	ISO 527-2
Tensile Creep Modulus (1 hr)	406000	psi	ISO 899-1
Tensile Creep Modulus (1000 hr)	218000	psi	ISO 899-1
Flexural Modulus	435000	psi	ISO 178
Poisson's Ratio	0.37		
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			ISO 179/1eA
-22°F	3.3	ft·lb/in <sup>2</sup>	
73°F	3.8	ft·lb/in <sup>2</sup>	
Charpy Unnotched Impact Strength			ISO 179/1eU
-22°F	95	ft·lb/in <sup>2</sup>	
73°F	95	ft·lb/in <sup>2</sup>	
Notched Izod Impact Strength			ISO 180/1A
-40°F	3.8	ft·lb/in <sup>2</sup>	
73°F	3.3	ft·lb/in <sup>2</sup>	
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness			ISO 2039-2
M-Scale	92		
R-Scale	120		
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (66 psi, Unannealed)	324	°F	ISO 75-2/B



Deflection Temperature Under Load (264 psi, Unannealed)	201 °F	ISO 75-2/A
Vicat Softening Temperature	320 °F	ISO 306/B50
Melting Temperature <sup>2</sup>	352 °F	ISO 11357-3
CLTE - Flow	6.7E-5 in/in/°F	ISO 11359-2
CLTE - Transverse	6.7E-5 in/in/°F	ISO 11359-2
RTI Elec		UL 746B
0.030 in	122 °F	
0.06 in	230 °F	
0.12 in	230 °F	
RTI Imp		UL 746B
0.030 in	122 °F	
0.06 in	185 °F	
0.12 in	194 °F	
RTI Str		UL 746B
0.030 in	122 °F	
0.06 in	194 °F	
0.12 in	203 °F	
Annealing Temperature	320 °F	
Annealing Time - Optional	30.0 min/mm	
<b>Electrical</b>	<b>Nominal Value Unit</b>	<b>Test Method</b>
Hot-wire Ignition (HWI) (0.0295 in)	8.0 sec	UL 746A
<b>Flammability</b>	<b>Nominal Value Unit</b>	<b>Test Method</b>
Flame Rating		UL 94
0.031 in	HB	
0.06 in	HB	
Flammability Classification		IEC 60695-11-10, -20
0.03 in	HB	
0.06 in	HB	
<b>Additional Information</b>	<b>Nominal Value Unit</b>	<b>Test Method</b>
Emission	< 8 ppm	VDA 275
Fogging		ISO 6452
F-value (refraction)	95 %	
G-value (condensate)	0.20 mg	

### Processing Information

	Nominal Value	Unit
<b>Injection</b>		
Drying Temperature	176	°F
Drying Time - Desiccant Dryer	2.0 to 4.0	hr
Suggested Max Moisture	< 0.20	%
Processing (Melt) Temp	410 to 428	°F
Melt Temperature, Optimum	419	°F
Mold Temperature	176 to 212	°F
Mold Temperature, Optimum	194	°F
Holding Pressure	11600 to 14500	psi
Drying Recommended	yes	
Hold Pressure Time	8.00	s/mm
Maximum Screw Tangential Speed	709	in/min

### Notes

<sup>1</sup> Typical properties: these are not to be construed as specifications.

<sup>2</sup> 10°C/min

