

**DURACON® M25-34**

Polyplastics - Acetal (POM) Copolymer

## General Information

**Product Description**

Extrusion Molding

For Extrusion

**General**

Material Status	• Commercial: Active
Availability	• Africa & Middle East • Europe • North America • Asia Pacific • Latin America
Features	• Copolymer
UL File Number	• E45034
Forms	• Pellets
Processing Method	• Extrusion • Injection Molding
Part Marking Code (ISO 11469)	• >POM<

 Properties <sup>1</sup>

Physical	Nominal Value	Unit	Test Method
Density	1.41	g/cm <sup>3</sup>	ISO 1183
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	2.5	g/10 min	ISO 1133
Melt Volume-Flow Rate (MVR) (190°C/2.16 kg)	2.2	cm <sup>3</sup> /10min	ISO 1133
Molding Shrinkage <sup>2</sup>			ISO 294-4
Across Flow : 0.0787 in	2.3	%	
Flow : 0.0787 in	2.7	%	
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	363000	psi	ISO 527-1
Tensile Stress	8560	psi	ISO 527-2
Nominal Tensile Strain at Break	40	%	ISO 527-2
Flexural Modulus	341000	psi	ISO 178
Flexural Stress	11700	psi	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (73°F)	3.8	ft-lb/in <sup>2</sup>	ISO 179/1eA
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (M-Scale)	80		ISO 2039-2
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (264 psi, Unannealed)	194	°F	ISO 75-2/A
CLTE - Flow (73 to 131°F)	6.7E-5	in/in/°F	Internal Method
CLTE - Transverse (73 to 131°F)	6.7E-5	in/in/°F	Internal Method
Electrical	Nominal Value	Unit	Test Method
Electric Strength (0.118 in)	480	V/mil	IEC 60243-1
Flammability	Nominal Value	Unit	Test Method
Flame Rating	HB		UL 94
Additional Information	Nominal Value	Unit	Test Method
Color Number	CF2001		

