

DELTRIN FG100 NC010

Delrin USA, LLC - Acetal (POM) Homopolymer

General Information
General

Material Status	• Commercial: Active
Availability	<ul style="list-style-type: none"> • Africa & Middle East • Asia Pacific • Europe • Latin America • North America
Features	<ul style="list-style-type: none"> • Good Processability • Good Strength • Good Thermal Stability • Good Toughness • High Viscosity • Homopolymer
RoHS Compliance	• Contact Manufacturer
Part Marking Code (ISO 11469)	• >POM<
Resin ID (ISO 1043)	• POM

Properties ¹

Physical	Nominal Value	Unit	Test Method
Density	1.42	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	2.3	g/10 min	ISO 1133
Melt Volume-Flow Rate (MVR) (190°C/2.16 kg)	1.9	cm ³ /10min	ISO 1133
Molding Shrinkage			ISO 294-4
Across Flow	1.9	%	
Flow	2.0	%	
Water Absorption (Saturation, 73°F, 0.0787 in)	0.90	%	ISO 62
Water Absorption (Equilibrium, 73°F, 0.0787 in, 50% RH)	0.20	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	435000	psi	ISO 527-1
Tensile Stress (Yield)	10300	psi	ISO 527-2
Tensile Strain (Yield)	25	%	ISO 527-2
Nominal Tensile Strain at Break	45	%	ISO 527-2
Tensile Creep Modulus (1 hr)	421000	psi	ISO 899-1
Tensile Creep Modulus (1000 hr)	232000	psi	ISO 899-1
Flexural Modulus	392000	psi	ISO 178
Poisson's Ratio	0.37		
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			ISO 179/1eA
-22°F	5.2	ft·lb/in ²	
73°F	7.1	ft·lb/in ²	
Charpy Unnotched Impact Strength			ISO 179/1eU
-22°F	No Break		
73°F	No Break		
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (66 psi, Unannealed)	329	°F	ISO 75-2/B
Deflection Temperature Under Load (264 psi, Unannealed)	208	°F	ISO 75-2/A
Melting Temperature ²	352	°F	ISO 11357-3
CLTE - Flow	6.1E-5	in/in/°F	ISO 11359-2
CLTE - Transverse	6.1E-5	in/in/°F	ISO 11359-2
RTI Elec			UL 746B
0.030 in	122	°F	
0.06 in	221	°F	
0.12 in	221	°F	
0.24 in	221	°F	



RTI Imp		UL 746B
0.030 in	122 °F	
0.06 in	185 °F	
0.12 in	185 °F	
0.24 in	185 °F	
RTI Str		UL 746B
0.030 in	122 °F	
0.06 in	194 °F	
0.12 in	194 °F	
0.24 in	194 °F	
Annealing Temperature	320 °F	
Annealing Time - Optional	30.0 min/mm	
Flammability	Nominal Value	Unit
Flame Rating		UL 94
0.030 in	HB	
0.06 in	HB	
Flammability Classification		IEC 60695-11-10, -20
0.030 in	HB	
0.06 in	HB	

Processing Information

Injection	Nominal Value	Unit
Drying Temperature	176	°F
Drying Time - Desiccant Dryer	2.0 to 4.0	hr
Suggested Max Moisture	0.20	%
Processing (Melt) Temp	410 to 428	°F
Melt Temperature, Optimum	419	°F
Mold Temperature	176 to 212	°F
Mold Temperature, Optimum	194	°F
Holding Pressure	13100 to 16000	psi
Drying Recommended	yes	
Hold Pressure Time	8.00	s/mm
Maximum Screw Tangential Speed	472	in/min
Extrusion	Nominal Value	Unit
Drying Temperature	176	°F
Drying Time	2.0 to 4.0	hr
Suggested Max Moisture	< 0.20	%
Melt Temperature	383 to 401	°F
Extrusion Melt Temperature, Optimum	392	°F

Notes

¹ Typical properties: these are not to be construed as specifications.

² 10°C/min

