

DURACON® M90-71

Polyplastics - Acetal (POM) Copolymer

General Information

Product Description

Special

Heat Resistant

General

Material Status	• Commercial: Active
Availability	• Africa & Middle East • Europe • North America • Asia Pacific • Latin America
Features	• Copolymer • Good Heat Resistance
UL File Number	• E45034
Forms	• Pellets
Processing Method	• Injection Molding
Part Marking Code (ISO 11469)	• >POM<

 Properties ¹

Physical	Nominal Value	Unit	Test Method
Density	1.41	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	9.0	g/10 min	ISO 1133
Melt Volume-Flow Rate (MVR) (190°C/2.16 kg)	8.0	cm ³ /10min	ISO 1133
Molding Shrinkage ²			ISO 294-4
Across Flow : 0.0787 in	2.1	%	
Flow : 0.0787 in	2.3	%	
Water Absorption (24 hr, 73°F, 0.0394 in)	0.60	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	392000	psi	ISO 527-1
Tensile Stress	8990	psi	ISO 527-2
Nominal Tensile Strain at Break	35	%	ISO 527-2
Flexural Modulus	363000	psi	ISO 178
Flexural Stress	12600	psi	ISO 178
Coefficient of Friction			JIS K7218
Dynamic ³	0.37		
vs. Steel - Dynamic ⁴	0.52		
Wear Factor			JIS K7218
71 psi, 59 ft/min ⁵	< 0.50	10 ⁻¹⁰ in ³ ·min/ft·lb·hr	
71 psi, 59 ft/min ⁶	50	10 ⁻¹⁰ in ³ ·min/ft·lb·hr	
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (73°F)	2.9	ft·lb/in ²	ISO 179/1eA
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (M-Scale)	90		ISO 2039-2
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (264 psi, Unannealed)	203	°F	ISO 75-2/A
CLTE - Flow (73 to 131°F)	6.7E-5	in/in/°F	Internal Method
CLTE - Transverse (73 to 131°F)	6.7E-5	in/in/°F	Internal Method
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+16	ohms	IEC 60093
Volume Resistivity	8.0E+13	ohms·cm	IEC 60093
Electric Strength (0.118 in)	480	V/mil	IEC 60243-1



Flammability	Nominal Value	Unit	Test Method
Flame Rating		HB	UL 94
Additional Information	Nominal Value	Unit	Test Method
Color Number		CF2001	

Notes

¹ Typical properties: these are not to be construed as specifications.

² 60x60x20mmt, Cavity Pressure 60 MPa

³ vs M90-44, 0.06 MPa, 15 cm/s

⁴ 0.49 MPa, 30 cm/s

⁵ vs C-Steel, Steel Side

⁶ vs C-Steel, Material Side

