

DURACON® SL-20

Polyplastics - Acetal (POM) Copolymer

General Information

Product Description

Special

Silicon oil concentrate

General

Material Status	<ul style="list-style-type: none"> Commercial: Active 		
Availability	<ul style="list-style-type: none"> Africa & Middle East Asia Pacific 	<ul style="list-style-type: none"> Europe Latin America 	<ul style="list-style-type: none"> North America
Additive	<ul style="list-style-type: none"> Silicone Lubricant 		
Features	<ul style="list-style-type: none"> Copolymer 	<ul style="list-style-type: none"> Lubricated 	
Forms	<ul style="list-style-type: none"> Pellets 		
Part Marking Code (ISO 11469)	<ul style="list-style-type: none"> >POM< 		

 Properties ¹

Physical	Nominal Value	Unit	Test Method
Water Absorption (24 hr, 73°F, 0.0394 in)	0.70	%	ISO 62
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (M-Scale)	75		ISO 2039-2
Thermal	Nominal Value	Unit	Test Method
CLTE - Flow (73 to 131°F)	7.2E-5	in/in/°F	Internal Method
CLTE - Transverse (73 to 131°F)	7.2E-5	in/in/°F	Internal Method
Additional Information	Nominal Value	Unit	Test Method
Color Number	CF2001		

Notes

¹ Typical properties: these are not to be construed as specifications.
