

Electrafil® POM CO AS BL334

 Techmer Polymer Modifiers - *Acetal (POM) Copolymer*
General Information

General	
Material Status	<ul style="list-style-type: none"> Commercial: Active
Availability	<ul style="list-style-type: none"> North America
Features	<ul style="list-style-type: none"> Conductive
Appearance	<ul style="list-style-type: none"> Blue
Processing Method	<ul style="list-style-type: none"> Injection Molding

Properties ¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	1.34		ASTM D792
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	300000	psi	ASTM D638
Tensile Strength (Yield)	7000	psi	ASTM D638
Tensile Elongation (Break)	50	%	ASTM D638
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (0.125 in)	1.6	ft-lb/in	ASTM D256
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+8 to 1.0E+11	ohms	ASTM D257

Processing Information

Injection	Nominal Value	Unit
Drying Temperature	180	°F
Drying Time	2.0 to 4.0	hr
Rear Temperature	325 to 360	°F
Middle Temperature	350 to 400	°F
Front Temperature	370 to 420	°F
Nozzle Temperature	350 to 380	°F
Processing (Melt) Temp	375 to 420	°F
Mold Temperature	140 to 175	°F
Injection Rate	Slow-Moderate	
Back Pressure	50.0 to 100	psi
Screw Speed	Slow-Moderate	

Notes

¹ Typical properties: these are not to be construed as specifications.

