

InLube® POMCAF10TF10SI2

Americhem - Acetal (POM) Copolymer

General Information
Product Description

10% ARAMID FIBER REINFORCED, 10% PTFE/2% SILICONE LUBRICATED ACETAL COPOLYMER

General

Material Status	• Commercial: Active		
Availability	• Africa & Middle East • Asia Pacific	• Europe • Latin America	• North America
Filler / Reinforcement	• Aramid Fiber, 10% Filler by Weight		
Additive	• PTFE Lubricant: 10%	• Silicone Lubricant: 2%	
Features	• Chemical Resistant • Good Mold Release	• Low Friction • Lubricated	• Wear Resistant
Uses	• Consumer Applications • Electrical/Electronic Applications	• Engineering Parts • Industrial Applications	• Office Automation Equipment
Forms	• Pellets		
Processing Method	• Injection Molding		

Properties ¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	1.44		ASTM D792
Molding Shrinkage - Flow	0.015 to 0.020	in/in	ASTM D955
Water Absorption (24 hr)	0.20	%	ASTM D570
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength	8150	psi	ASTM D638
Tensile Elongation (Yield)	10 to 15	%	ASTM D638
Flexural Modulus	450000	psi	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (0.125 in)	1.3	ft·lb/in	ASTM D256
Unnotched Izod Impact (0.125 in)	8.0 to 10	ft·lb/in	ASTM D4812
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (264 psi, Unannealed)	220	°F	ASTM D648
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	> 1.0E+14	ohms	

Processing Information

Injection	Nominal Value	Unit
Drying Temperature	180	°F
Drying Time	4.0	hr
Processing (Melt) Temp	375 to 410	°F
Mold Temperature	180 to 220	°F
Back Pressure	25.0 to 50.0	psi
Screw Speed	30 to 60	rpm
Vent Depth	5.0E-4 to 1.0E-3	in

