

InLube® POMCCF20TF15

Americhem - Acetal (POM) Copolymer

General Information

Product Description

20% CARBON FIBER REINFORCED 15% PTFE LUBRICATED COPOLYMER ACETAL

General

Material Status	• Commercial: Active		
Availability	• Africa & Middle East	• Europe	• North America
	• Asia Pacific	• Latin America	
Filler / Reinforcement	• Carbon Fiber, 20% Filler by Weight		
Additive	• PTFE Lubricant: 15%		
Features	• Chemical Resistant	• Good Mold Release	• Low Friction
	• Filled	• High Stiffness	• Lubricated
	• Good Dimensional Stability	• High Strength	• Wear Resistant
Uses	• Consumer Applications	• Engineering Parts	• Industrial Applications
	• Electrical/Electronic Applications	• Household Goods	• Office Automation Equipment
Forms	• Pellets		
Processing Method	• Injection Molding		

 Properties ¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	1.55		ASTM D792
Specific Volume	17.9	in ³ /lb	
Molding Shrinkage - Flow	5.0E-3 to 7.0E-3	in/in	ASTM D955
Water Absorption (24 hr)	0.50	%	ASTM D570
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength	21000	psi	ASTM D638
Tensile Elongation (Yield)	1.0 to 2.0	%	ASTM D638
Flexural Modulus	1.80E+6	psi	ASTM D790
Flexural Strength	22000	psi	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (0.125 in)	0.80	ft·lb/in	ASTM D256
Unnotched Izod Impact (0.125 in)	6.0	ft·lb/in	ASTM D4812
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (264 psi, Unannealed)	320	°F	ASTM D648
CLTE - Flow	2.2E-5	in/in/°F	ASTM D696
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+3 to 1.0E+7	ohms	
Flammability	Nominal Value	Unit	Test Method
Flame Rating (0.06 in)	HB		UL 94

Processing Information

Injection	Nominal Value	Unit
Drying Temperature	180	°F
Drying Time	4.0	hr
Processing (Melt) Temp	375 to 410	°F
Mold Temperature	200	°F
Back Pressure	50.0 to 100	psi
Screw Speed	30 to 60	rpm
Vent Depth	5.0E-4 to 1.0E-3	in

