

HiFill® POM HO GF10 CC

Techmer Polymer Modifiers - Acetal (POM) Homopolymer

General Information
General

Material Status	• Commercial: Active
Availability	• North America
Filler / Reinforcement	• Glass Fiber
Features	• Chemically Coupled • Homopolymer
Appearance	• Colors Available
Processing Method	• Injection Molding

Properties ¹

	Nominal Value	Unit	Test Method
Physical			
Density / Specific Gravity	1.48		ASTM D792
Molding Shrinkage - Flow (0.125 in)	7.0E-3	in/in	ASTM D955
Water Absorption (24 hr)	0.040	%	ASTM D570
Mechanical			
Tensile Strength (Break)	9300	psi	ASTM D638
Tensile Elongation (Break)	3.0	%	ASTM D638
Flexural Modulus	595000	psi	ASTM D790
Flexural Strength	13000	psi	ASTM D790
Impact			
Notched Izod Impact (73°F, 0.125 in)	1.0	ft·lb/in	ASTM D256
Hardness			
Rockwell Hardness (R-Scale)	82		ASTM D785
Thermal			
Deflection Temperature Under Load (66 psi, Unannealed)	337	°F	ASTM D648
Deflection Temperature Under Load (264 psi, Unannealed)	299	°F	ASTM D648
Melting Temperature	351	°F	
CLTE - Flow	2.6E-5	in/in/°F	ASTM D696
Electrical			
Volume Resistivity	1.0E+14	ohms·cm	ASTM D257
Dielectric Strength (Method A (Short-Time))	410	V/mil	ASTM D149
Flammability			
Flame Rating (0.06 in)	HB		UL 94

Processing Information

	Nominal Value	Unit
Injection		
Drying Temperature	200	°F
Drying Time	2.0 to 3.0	hr
Rear Temperature	380 to 425	°F
Middle Temperature	380 to 425	°F
Front Temperature	380 to 425	°F
Processing (Melt) Temp	380 to 440	°F
Mold Temperature	180 to 220	°F
Back Pressure	50.0 to 100	psi
Screw Speed	30 to 60	rpm

