

**LATILUB 73/13-15T G/15**

 LATI INDUSTRIA TERMOPLASTICI SPA - *Acetal (POM) Copolymer*

## General Information

**Product Description**

Self-lubricating product based on Polyoximethylene (POM). PTFE. Glass fibres.

**General**

Material Status	• Commercial: Active		
Availability	• Africa & Middle East	• Europe	• North America
	• Asia Pacific	• Latin America	
Filler / Reinforcement	• Glass Fiber		
Additive	• PTFE Lubricant		
Features	• Lubricated	• Self Lubricating	

 Properties <sup>1</sup>

Physical	Nominal Value	Unit	Test Method
Density (73°F)	1.59	g/cm <sup>3</sup>	ISO 1183
Molding Shrinkage <sup>2</sup>			ISO 294-4
Across Flow : 0.0787 in	1.0 to 1.2	%	
Flow : 0.0787 in	0.70 to 1.0	%	
Water Absorption <sup>3</sup> (Saturation, 73°F)	0.15	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus (73°F)	812000	psi	ISO 527-1/1
Tensile Stress (Break, 73°F)	10900	psi	ISO 527-2/5
Tensile Strain (Break, 73°F)	2.8	%	ISO 527-2/5
Coefficient of Friction <sup>4</sup>			Internal Method
Dynamic	0.34		
Static	0.29		
Wear Factor <sup>5</sup>	1700	10 <sup>-4</sup> -10 <sup>-5</sup> in <sup>3</sup> ·min/ft·lb·hr	Internal Method
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			ISO 179/1eA
-4°F	2.4	ft·lb/in <sup>2</sup>	
73°F	2.4	ft·lb/in <sup>2</sup>	
Charpy Unnotched Impact Strength			ISO 179/1eU
-4°F	12	ft·lb/in <sup>2</sup>	
73°F	12	ft·lb/in <sup>2</sup>	
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (66 psi, Unannealed)	320	°F	ISO 75-2/B
Deflection Temperature Under Load (264 psi, Unannealed)	311	°F	ISO 75-2/A
Vicat Softening Temperature	302	°F	ISO 306/B120
CLTE - Flow (86 to 212°F)	4.2E-5	in/in/°F	ISO 11359-2
CLTE - Transverse (86 to 212°F)	5.6E-5	in/in/°F	ISO 11359-2
Thermal Conductivity			ASTM E1461
-- <sup>6</sup>	2.1	Btu·in/hr/ft <sup>2</sup> /°F	
-- <sup>7</sup>	2.1	Btu·in/hr/ft <sup>2</sup> /°F	
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+12	ohms	ASTM D257
Dielectric Strength (73°F, 0.0787 in, Method A (Short-Time))	480	V/mil	ASTM D149
Comparative Tracking Index <sup>8</sup> (Solution A)	600	V	IEC 60112

**Flammability**
**Nominal Value Unit**
**Test Method**


Flame Rating		UL 94
0.06 in	HB	
0.12 in	HB	

#### Notes

<sup>1</sup> Typical properties: these are not to be construed as specifications.

<sup>2</sup> 60 MPa

<sup>3</sup> in air

<sup>4</sup> ISO 7148-2 (speed 0.126 m/s, load 10N)

<sup>5</sup> ISO 7148-2 (speed 0.126 m/s, load 10N, path length 13.6km)

<sup>6</sup> through plane

<sup>7</sup> in plane

<sup>8</sup> without surfactant

