

InStruc® POMCGF20CC

Americhem - Acetal (POM) Copolymer

General Information
Product Description

20% GLASS FIBER REINFORCED, CHEMICALLY COUPLED COPOLYMER ACETAL

General

Material Status	• Commercial: Active		
Availability	• Africa & Middle East	• Europe	• North America
	• Asia Pacific	• Latin America	
Filler / Reinforcement	• Glass Fiber, 20% Filler by Weight		
Features	• Chemically Coupled	• Good Dimensional Stability	• High Strength
	• Filled	• High Stiffness	• UV Stabilized
Uses	• Closures	• Engineering Parts	• Office Automation Equipment
	• Consumer Applications	• Household Goods	• Outdoor Applications
	• Electrical/Electronic Applications	• Industrial Applications	• Window & Door Components
Forms	• Pellets		
Processing Method	• Injection Molding		

Properties ¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	1.54		ASTM D792
Molding Shrinkage - Flow	4.0E-3 to 8.0E-3	in/in	ASTM D955
Water Absorption (24 hr)	0.30	%	ASTM D570
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	950000	psi	ASTM D638
Tensile Strength	14000	psi	ASTM D638
Tensile Elongation (Yield)	2.0 to 4.0	%	ASTM D638
Flexural Modulus	850000	psi	ASTM D790
Flexural Strength	20000	psi	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (0.125 in)	1.2	ft·lb/in	ASTM D256
Unnotched Izod Impact (0.125 in)	10	ft·lb/in	ASTM D4812
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (264 psi, Unannealed)	310	°F	ASTM D648

Processing Information

Injection	Nominal Value	Unit
Drying Temperature	180	°F
Drying Time	4.0	hr
Processing (Melt) Temp	375 to 410	°F
Mold Temperature	200	°F
Back Pressure	50.0 to 100	psi
Screw Speed	30 to 60	rpm
Vent Depth	5.0E-4 to 1.0E-3	in

