

LATIOHM 73-09 PD01 G/20

 LATI INDUSTRIA TERMOPLASTICI SPA - *Acetal (POM) Copolymer*
General Information
Product Description

Semiconductive/dissipative product based on Polyoximethylene (POM). Glass fibres. PFAS-free product.

General

Material Status	• Commercial: Active
Availability	• Africa & Middle East • Asia Pacific • Europe • Latin America • North America
Filler / Reinforcement	• Glass Fiber
Features	• Antistatic • Electrically Conductive • PFAS Free

Properties ¹

Physical	Nominal Value	Unit	Test Method
Density (73°F)	1.54	g/cm ³	ISO 1183
Molding Shrinkage ²			ISO 294-4
Across Flow : 0.0787 in	0.80 to 1.3	%	
Flow : 0.0787 in	0.40 to 0.65	%	
Water Absorption ³ (Saturation, 73°F)	0.15	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus (73°F)	1.74E+6	psi	ISO 527-1/1
Tensile Stress (Break, 73°F)	15200	psi	ISO 527-2/5
Tensile Strain (Break, 73°F)	1.2	%	ISO 527-2/5
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (73°F)	2.9	ft·lb/in ²	ISO 179/1eA
Charpy Unnotched Impact Strength (73°F)	14	ft·lb/in ²	ISO 179/1eU
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (66 psi, Unannealed)	320	°F	ISO 75-2/B
Deflection Temperature Under Load (264 psi, Unannealed)	311	°F	ISO 75-2/A
Vicat Softening Temperature	320	°F	ISO 306/B120
CLTE - Flow (86 to 212°F)	1.7E-5	in/in/°F	ISO 11359-2
CLTE - Transverse (86 to 212°F)	4.2E-5	in/in/°F	ISO 11359-2
Thermal Conductivity			ASTM E1461
⁴	2.8	Btu·in/hr/ft ² /°F	
⁵	3.5	Btu·in/hr/ft ² /°F	
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	2.0E+2	ohms	ASTM D257
Volume Resistivity	1.0E+3	ohms·cm	ASTM D257
Flammability	Nominal Value	Unit	Test Method
Flame Rating			UL 94
0.06 in		HB	
0.12 in		HB	

