

Plaslube® J-80/20/TF/15

 Techmer Polymer Modifiers - *Acetal (POM) Copolymer*
General Information
General

Material Status	• Commercial: Active
Availability	• Africa & Middle East • Europe • North America • Asia Pacific • Latin America
Filler / Reinforcement	• Glass Fiber, 20% Filler by Weight
Additive	• PTFE Lubricant: 15%
Features	• Chemical Resistant • Good Stiffness • Lubricated
RoHS Compliance	• RoHS Compliant
Forms	• Pellets
Processing Method	• Injection Molding

Properties ¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	1.63		ASTM D792
Molding Shrinkage - Flow	3.0E-3	in/in	ASTM D955
Water Absorption (24 hr)	0.26	%	ASTM D570
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	900000	psi	ASTM D638
Tensile Strength (Yield)	8500	psi	ASTM D638
Tensile Elongation (Yield)	2.4	%	ASTM D638
Flexural Modulus	860000	psi	ASTM D790
Flexural Strength (Yield)	12700	psi	ASTM D790
Coefficient of Friction (vs. Steel - Static)	0.20		ASTM D1894
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	0.80	ft·lb/in	ASTM D256
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (M-Scale)	57		ASTM D785
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (66 psi, Unannealed)	326	°F	ASTM D648
Deflection Temperature Under Load (264 psi, Unannealed)	320	°F	ASTM D648
CLTE - Flow	3.8E-5	in/in/°F	ASTM D696

Processing Information

Injection	Nominal Value	Unit
Rear Temperature	350 to 380	°F
Middle Temperature	370 to 410	°F
Front Temperature	360 to 390	°F
Nozzle Temperature	350 to 400	°F
Processing (Melt) Temp	380 to 420	°F
Mold Temperature	180 to 250	°F

