

**Plaslube® AC-80/TF/15**

 Techmer Polymer Modifiers - *Acetal (POM) Copolymer*

## General Information

**Product Description**

TES10789

**General**

Material Status	• Commercial: Active
Availability	• Africa & Middle East • Asia Pacific • Europe • Latin America • North America
Additive	• PTFE Lubricant: 15%
Features	• Lubricated
Uses	• Bearings • Gears
RoHS Compliance	• RoHS Compliant
Forms	• Pellets
Processing Method	• Injection Molding

 Properties <sup>1</sup>

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	1.49		ASTM D792
Molding Shrinkage - Flow	0.020	in/in	ASTM D955
Water Absorption (24 hr)	0.23	%	ASTM D570
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Break, 73°F)	6300	psi	ASTM D638
Flexural Modulus (73°F)	310000	psi	ASTM D790
Flexural Strength (Break, 73°F)	9600	psi	ASTM D790
Coefficient of Friction			ASTM D1894
vs. Steel - Dynamic	0.16		
vs. Steel - Static	0.080		
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (73°F, 0.125 in)	0.90	ft·lb/in	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (264 psi, Unannealed)	215	°F	ASTM D648
CLTE - Flow	1.4E-5	in/in/°F	ASTM D696
Additional Information			
Coefficient of Friction, Static, Thrust washer, 40psi, ambient temp.: 0.08			
Coefficient of Friction, Dynamic, Thrust washer, 40psi, 50 ft/min, ambient temp.: 0.16			
Limiting PV, Thrust washer, 100 FPM, ambient temp.: 1.2E4			

## Processing Information

Injection	Nominal Value	Unit
Drying Temperature	180	°F
Drying Time	1.0 to 2.0	hr
Suggested Max Moisture	0.20	%
Rear Temperature	350 to 370	°F
Middle Temperature	370 to 390	°F
Front Temperature	360 to 380	°F
Nozzle Temperature	350 to 370	°F
Processing (Melt) Temp	370 to 400	°F
Mold Temperature	170 to 200	°F
Injection Rate	Moderate-Fast	
Back Pressure	50.0 to 100	psi

**Injection Notes**


---

Screw Speed: Medium

Recommendations for Molding and Tool Conditions: Well vented

Moisture Content, as received: Product is packaged at 0.2% or less.

Drying not normally required. Dry at 180°F for 1 to 2 hours if necessary.

---

#### Notes

---

<sup>1</sup> Typical properties: these are not to be construed as specifications.

---

