

Plaslube® POM CO GM30 TL5

Techmer Polymer Modifiers - Acetal (POM) Copolymer

General Information
General

Material Status	• Commercial: Active
Availability	• North America
Filler / Reinforcement	• Milled Glass Fiber, 30% Filler by Weight
Additive	• PTFE Lubricant: 5%
Features	• Copolymer • Lubricated
Appearance	• Colors Available
Forms	• Pellets
Processing Method	• Injection Molding

Properties ¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	1.63		ASTM D792
Water Absorption (24 hr)	0.30	%	ASTM D570
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Break)	6500	psi	ASTM D638
Tensile Elongation (Break)	2.0	%	ASTM D638
Flexural Modulus	700000	psi	ASTM D790
Flexural Strength	11000	psi	ASTM D790
Coefficient of Friction			ASTM D1894
vs. Steel - Dynamic	0.18		
vs. Steel - Static	0.12		
Wear Factor	40	10 ⁻¹⁰ in ³ ·min/ft·lb·hr	ASTM D3702
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (73°F, 0.125 in)	0.70	ft·lb/in	ASTM D256
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	110		ASTM D785
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (66 psi, Unannealed)	300	°F	ASTM D648
Deflection Temperature Under Load (264 psi, Unannealed)	290	°F	ASTM D648
CLTE - Flow	3.0E-5	in/in/°F	ASTM D696
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	1.0E+15	ohms·cm	ASTM D257
Dielectric Strength (Method A (Short-Time))	450	V/mil	ASTM D149
Flammability	Nominal Value	Unit	Test Method
Flame Rating	HB		UL 94

Processing Information

Injection	Nominal Value	Unit
Drying Temperature	160	°F
Drying Time	1.0	hr
Rear Temperature	350 to 380	°F
Middle Temperature	370 to 410	°F
Front Temperature	360 to 390	°F
Nozzle Temperature	350 to 400	°F
Processing (Melt) Temp	380 to 420	°F
Mold Temperature	180 to 250	°F

