

**TENAC™-C 7513**

Asahi Kasei Corporation - Acetal (POM) Copolymer

**General Information**

<b>General</b>			
Material Status	• Commercial: Active		
Availability	• Africa & Middle East	• Europe	• North America
	• Asia Pacific	• Latin America	
Features	• Good Weather Resistance	• High Flow	• UV Resistant
Uses	• Automotive Interior Parts	• Gears	
	• Engineering Parts	• Housings	
Automotive Specifications	• VOLKSWAGEN KTHD 041 Color: Black	• VOLKSWAGEN KTHD0000000J51 Color: Lagune	
Part Marking Code (ISO 11469)	• >POM<		

**Properties <sup>1</sup>**

<b>Physical</b>	<b>Nominal Value</b>	<b>Unit</b>	<b>Test Method</b>
Density / Specific Gravity	1.41		ASTM D792
Density	1.41	g/cm <sup>3</sup>	ISO 1183
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	30	g/10 min	ISO 1133
Molding Shrinkage - Flow	0.016 to 0.020	in/in	Internal Method
Water Absorption (24 hr, 73°F, 50% RH)	0.20	%	ASTM D570
<b>Mechanical</b>	<b>Nominal Value</b>	<b>Unit</b>	<b>Test Method</b>
Tensile Modulus	399000	psi	ISO 527-1
Tensile Strength	9280	psi	ASTM D638
Tensile Stress (Yield)	9280	psi	ISO 527-2
Tensile Elongation (Break)	30	%	ASTM D638
Nominal Tensile Strain at Break	30	%	ISO 527-2
Flexural Modulus	377000	psi	ASTM D790
Flexural Modulus	377000	psi	ISO 178
Flexural Strength	13500	psi	ASTM D790
Taber Abrasion Resistance	14.0	mg	ASTM D1044
<b>Impact</b>	<b>Nominal Value</b>	<b>Unit</b>	<b>Test Method</b>
Charpy Notched Impact Strength	2.4	ft·lb/in <sup>2</sup>	ISO 179
Notched Izod Impact	1.0	ft·lb/in	ASTM D256
<b>Hardness</b>	<b>Nominal Value</b>	<b>Unit</b>	<b>Test Method</b>
Rockwell Hardness			ASTM D785
M-Scale	80		
R-Scale	115		
<b>Thermal</b>	<b>Nominal Value</b>	<b>Unit</b>	<b>Test Method</b>
Deflection Temperature Under Load (66 psi, Unannealed)	316	°F	ASTM D648
Deflection Temperature Under Load (66 psi, Unannealed)	313	°F	ISO 75-2/B
Deflection Temperature Under Load (264 psi, Unannealed)	230	°F	ASTM D648
Deflection Temperature Under Load (264 psi, Unannealed)	212	°F	ISO 75-2/A
CLTE - Flow	5.6E-5	in/in/°F	ASTM D696
CLTE - Flow	5.6E-5	in/in/°F	ISO 11359-2
<b>Electrical</b>	<b>Nominal Value</b>	<b>Unit</b>	<b>Test Method</b>
Surface Resistivity	1.0E+16 to 1.0E+17	ohms	ASTM D257
Volume Resistivity (73°F)	1.0E+15 to 1.0E+16	ohms·cm	ASTM D257
Dielectric Strength	480	V/mil	ASTM D149
Arc Resistance	250	sec	ASTM D495



## Processing Information

Injection	Nominal Value	Unit
Drying Temperature - Hot Air Dryer	176 to 194	°F
Drying Time - Hot Air Dryer	3.0 to 4.0	hr
Processing (Melt) Temp	356 to 410	°F
Mold Temperature	> 140	°F

### Notes

<sup>1</sup> Typical properties: these are not to be construed as specifications.

