

TENAC™ -C EF750

Asahi Kasei Corporation - Acetal (POM) Copolymer

General Information

General			
Material Status	• Commercial: Active		
Availability	• Africa & Middle East	• Europe	• North America
	• Asia Pacific	• Latin America	
Additive	• Antistatic		
Features	• Electrically Conductive	• High Flow	
Uses	• Bearings	• Gears	
	• Engineering Parts	• Housings	
Part Marking Code (ISO 11469)	• >POM-CD<		

Properties ¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	1.41		ASTM D792
Density	1.41	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	10	g/10 min	ISO 1133
Molding Shrinkage - Flow	0.016 to 0.020	in/in	Internal Method
Water Absorption (24 hr, 73°F, 50% RH)	0.20	%	ASTM D570
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	377000	psi	ISO 527-1
Tensile Strength	6960	psi	ASTM D638
Tensile Stress (Break)	7540	psi	ISO 527-2
Tensile Elongation (Break)	10	%	ASTM D638
Nominal Tensile Strain at Break	10	%	ISO 527-2
Flexural Modulus	355000	psi	ASTM D790
Flexural Modulus	363000	psi	ISO 178
Flexural Strength	11300	psi	ASTM D790
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength	1.4	ft·lb/in ²	ISO 179
Notched Izod Impact	0.79	ft·lb/in	ASTM D256
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (M-Scale)	80		ASTM D785
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (66 psi, Unannealed)	324	°F	ASTM D648
Deflection Temperature Under Load (66 psi, Unannealed)	324	°F	ISO 75-2/B
Deflection Temperature Under Load (264 psi, Unannealed)	248	°F	ASTM D648
Deflection Temperature Under Load (264 psi, Unannealed)	212	°F	ISO 75-2/A
CLTE - Flow	5.6E-5	in/in/°F	ASTM D696
CLTE - Flow	3.3E-5	in/in/°F	ISO 11359-2
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+2 to 1.0E+4	ohms	ASTM D257
Surface Resistivity	--	10 to 1.0E+2 ohms	JIS K7194
Surface Resistivity	--	10 to 1.0E+2 ohms	IEC 60093
Volume Resistivity (73°F)	1.0E+2 to 1.0E+4	ohms·cm	ASTM D257
Volume Resistivity	--	10 to 1.0E+2 ohms·cm	IEC 60093
Volume Resistivity	--	10 to 1.0E+2 ohms·cm	JIS K7194



Flammability	Nominal Value	Unit	Test Method
Flame Rating			UL 94
0.030 in		HB	
0.06 in		HB	

Processing Information

Injection	Nominal Value	Unit
Drying Temperature - Hot Air Dryer	176 to 194	°F
Drying Time - Hot Air Dryer	3.0 to 4.0	hr
Processing (Melt) Temp	356 to 410	°F
Mold Temperature	> 140	°F

Notes

¹ Typical properties: these are not to be construed as specifications.

