

## AuroraGuard™ F01001

Aurora Material Solutions, LLC - Polypropylene Homopolymer

### General Information

#### Product Description

Flame Retardant Polypropylene

Formerly known as EnDure F01001

#### General

Material Status	• Commercial: Active		
Availability	• Africa & Middle East	• Europe	• North America
	• Asia Pacific	• Latin America	
Additive	• Flame Retardant		
Features	• Flame Retardant		
Uses	• Automotive Applications	• Electrical/Electronic Applications	• Material Handling
Appearance	• Black	• Colors Available	• Natural Color
Processing Method	• Injection Molding	• Profile Extrusion	

### Properties <sup>1</sup>

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	0.992		ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	10	g/10 min	ASTM D1238
Molding Shrinkage - Flow (0.126 in)	0.016 to 0.022	in/in	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	5080	psi	ASTM D638
Flexural Modulus	209000	psi	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (73°F)	0.51	ft-lb/in	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (66 psi, Unannealed)	205	°F	ASTM D648
Flammability	Nominal Value	Unit	Test Method
Flame Rating (0.06 in)	V-0		UL 94

### Processing Information

Injection	Nominal Value	Unit
Rear Temperature	350 to 400	°F
Middle Temperature	390 to 450	°F
Front Temperature	390 to 450	°F
Nozzle Temperature	390 to 450	°F
Processing (Melt) Temp	350 to 400	°F
Mold Temperature	100 to 150	°F

