

AuroraGuard™ F02001

Aurora Material Solutions, LLC - Polypropylene

General Information

Product Description

Polypropylene, UL94 V0 Rated

Formerly known as EnDure F02001

General

Material Status	• Commercial: Active		
Availability	• Africa & Middle East • Asia Pacific	• Europe • Latin America	• North America
Uses	• Automotive Applications	• Lawn & Garden Equipment	• Material Handling
Appearance	• Black	• Colors Available	• Natural Color
Processing Method	• Injection Molding	• Profile Extrusion	

Properties ¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	0.990		ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	20	g/10 min	ASTM D1238
Molding Shrinkage - Flow (0.126 in)	0.016 to 0.022	in/in	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	5000	psi	ASTM D638
Flexural Modulus	210000	psi	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (73°F)	0.50	ft-lb/in	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (66 psi, Unannealed)	205	°F	ASTM D648
Flammability	Nominal Value	Unit	Test Method
Flame Rating			UL 94
0.06 in	V-0		
0.12 in	V-0		

Processing Information

Injection	Nominal Value	Unit
Rear Temperature	350 to 400	°F
Middle Temperature	390 to 450	°F
Front Temperature	390 to 450	°F
Nozzle Temperature	390 to 450	°F
Processing (Melt) Temp	350 to 400	°F
Mold Temperature	100 to 150	°F

Notes

¹ Typical properties: these are not to be construed as specifications.

