

AuroraGuard™ F020TF0801U

Aurora Material Solutions, LLC - Polypropylene

General Information
Product Description

20% Talc Reinforced, Flame Retardant Extrusion Grade PP, UV Stabilized

Formerly known as EnDure F020TF0801U

General

Material Status	• Commercial: Active		
Availability	• Africa & Middle East	• Europe	• North America
	• Asia Pacific	• Latin America	
Filler / Reinforcement	• Talc, 20% Filler by Weight		
Additive	• Flame Retardant	• UV Stabilizer	
Features	• Flame Retardant	• UV Stabilized	
Uses	• Automotive Applications	• Lawn & Garden Equipment	• Material Handling
Appearance	• Black	• Colors Available	• Natural Color
Processing Method	• Injection Molding	• Profile Extrusion	

Properties ¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	1.37		ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	8.0	g/10 min	ASTM D1238
Molding Shrinkage - Flow (0.126 in)	9.0E-3 to 0.013	in/in	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	3500	psi	ASTM D638
Tensile Strength (Break)	3000	psi	ASTM D638
Tensile Elongation (Break)	5.0	%	ASTM D638
Flexural Modulus	325000	psi	ASTM D790
Flexural Strength	6000	psi	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (73°F)	1.0	ft·lb/in	ASTM D256
Flammability	Nominal Value	Unit	Test Method
Flame Rating (0.13 in)	V-0		UL 94

Processing Information

Extrusion	Nominal Value	Unit
Melt Temperature	350 to 450	°F

