

HiFill® PP 0096 S2 LE

Techmer Polymer Modifiers - *Polypropylene*

General Information

General

Material Status	• Commercial: Active
Availability	• North America
Filler / Reinforcement	• Filler
Features	• Low Extractables
Agency Ratings	• FDA
Appearance	• Colors Available
Forms	• Pellets
Processing Method	• Injection Molding

Properties ¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	0.960		ASTM D792
Molding Shrinkage - Flow (0.125 in)	0.019	in/in	ASTM D955
Water Absorption (24 hr)	0.050	%	ASTM D570
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	4800	psi	ASTM D638
Tensile Elongation (Break)	10	%	ASTM D638
Flexural Modulus	190000	psi	ASTM D790
Flexural Strength	5200	psi	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (73°F, 0.125 in)	0.50	ft·lb/in	ASTM D256
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	120		ASTM D785
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (66 psi, Unannealed)	240	°F	ASTM D648
Deflection Temperature Under Load (264 psi, Unannealed)	130	°F	ASTM D648
CLTE - Flow	1.9E-5	in/in/°F	ASTM D696

Notes

¹ Typical properties: these are not to be construed as specifications.

