

HiFill® PP 0254 S1

 Techmer Polymer Modifiers - *Polypropylene*
General Information
General

Material Status	<ul style="list-style-type: none"> Commercial: Active
Availability	<ul style="list-style-type: none"> North America
Filler / Reinforcement	<ul style="list-style-type: none"> Filler
Appearance	<ul style="list-style-type: none"> Colors Available
Forms	<ul style="list-style-type: none"> Pellets
Processing Method	<ul style="list-style-type: none"> Injection Molding

Properties ¹

	Nominal Value	Unit	Test Method
Physical			
Density / Specific Gravity	2.54		ASTM D792
Molding Shrinkage - Flow (0.125 in)	3.0E-3	in/in	ASTM D955
Water Absorption (24 hr)	0.050	%	ASTM D570
Mechanical			
Nominal Value Unit Test Method			
Tensile Strength (Yield)	3800	psi	ASTM D638
Tensile Elongation (Break)	2.0	%	ASTM D638
Flexural Modulus	750000	psi	ASTM D790
Flexural Strength	5200	psi	ASTM D790
Impact			
Nominal Value Unit Test Method			
Notched Izod Impact (73°F, 0.125 in)	0.50	ft-lb/in	ASTM D256
Hardness			
Nominal Value Unit Test Method			
Rockwell Hardness (R-Scale)	120		ASTM D785
Thermal			
Nominal Value Unit Test Method			
Deflection Temperature Under Load (66 psi, Unannealed)	240	°F	ASTM D648
Deflection Temperature Under Load (264 psi, Unannealed)	130	°F	ASTM D648
CLTE - Flow	1.9E-5	in/in/°F	ASTM D696
Electrical			
Nominal Value Unit Test Method			
Volume Resistivity	1.0E+5	ohms·cm	ASTM D257

Notes
¹ Typical properties: these are not to be construed as specifications.
