

HiFill FR® PP FR-N X BKN001

Techmer Polymer Modifiers - *Polypropylene*

General Information

General

Material Status	• Commercial: Active
Availability	• North America
Features	• Flame Retardant
Appearance	• Black
Forms	• Pellets
Processing Method	• Injection Molding

Properties ¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	1.01		ASTM D792
Molding Shrinkage - Flow (0.125 in)	0.014	in/in	ASTM D955
Water Absorption (24 hr)	0.040	%	ASTM D570
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	3600	psi	ASTM D638
Tensile Elongation (Yield)	40	%	ASTM D638
Flexural Modulus	195000	psi	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (0.125 in)	1.8	ft-lb/in	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (66 psi, Unannealed)	205	°F	ASTM D648
Deflection Temperature Under Load (264 psi, Unannealed)	155	°F	ASTM D648
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	1.0E+16	ohms·cm	ASTM D257
Dielectric Strength (Method A (Short-Time))	450	V/mil	ASTM D149
Flammability	Nominal Value	Unit	Test Method
Flame Rating (0.13 in)	V-0		UL 94

Processing Information

Injection	Nominal Value	Unit
Drying Temperature	170	°F
Drying Time	2.0 to 3.0	hr
Rear Temperature	420 to 460	°F
Middle Temperature	420 to 460	°F
Front Temperature	420 to 460	°F
Processing (Melt) Temp	390 to 440	°F
Mold Temperature	80 to 120	°F
Back Pressure	50.0 to 100	psi
Screw Speed	30 to 60	rpm

Notes

¹ Typical properties: these are not to be construed as specifications.

