

**HiFill® PP 0159 B**

 Techmer Polymer Modifiers - *Polypropylene*
**General Information**
**General**

Material Status	<ul style="list-style-type: none"> <li>Commercial: Active</li> </ul>
Availability	<ul style="list-style-type: none"> <li>North America</li> </ul>
Filler / Reinforcement	<ul style="list-style-type: none"> <li>Filler</li> </ul>
Appearance	<ul style="list-style-type: none"> <li>Colors Available</li> </ul>
Forms	<ul style="list-style-type: none"> <li>Pellets</li> </ul>
Processing Method	<ul style="list-style-type: none"> <li>Injection Molding</li> </ul>

**Properties <sup>1</sup>**

<b>Physical</b>	<b>Nominal Value</b>	<b>Unit</b>	<b>Test Method</b>
Density / Specific Gravity	1.59		ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	10	g/10 min	ASTM D1238
Molding Shrinkage - Flow (0.125 in)	0.015	in/in	ASTM D955
Water Absorption (24 hr)	0.050	%	ASTM D570
<b>Mechanical</b>	<b>Nominal Value</b>	<b>Unit</b>	<b>Test Method</b>
Tensile Strength (Yield)	2700	psi	ASTM D638
Tensile Elongation (Break)	20	%	ASTM D638
Flexural Modulus	390000	psi	ASTM D790
Flexural Strength	5000	psi	ASTM D790
<b>Impact</b>	<b>Nominal Value</b>	<b>Unit</b>	<b>Test Method</b>
Notched Izod Impact (73°F, 0.125 in)	0.50	ft·lb/in	ASTM D256
<b>Hardness</b>	<b>Nominal Value</b>	<b>Unit</b>	<b>Test Method</b>
Rockwell Hardness (R-Scale)	95		ASTM D785
<b>Thermal</b>	<b>Nominal Value</b>	<b>Unit</b>	<b>Test Method</b>
Deflection Temperature Under Load (66 psi, Unannealed)	225	°F	ASTM D648
Deflection Temperature Under Load (264 psi, Unannealed)	145	°F	ASTM D648
CLTE - Flow	1.9E-5	in/in/°F	ASTM D696

**Notes**
<sup>1</sup> Typical properties: these are not to be construed as specifications.
