

HiFill® PP GB30 BK

 Techmer Polymer Modifiers - *Polypropylene*
General Information
General

Material Status	• Commercial: Active
Availability	• North America
Filler / Reinforcement	• Glass Bead, 30% Filler by Weight
Appearance	• Black
Processing Method	• Injection Molding

Properties ¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	1.12		ASTM D792
Melt Mass-Flow Rate (MFR) (300°C/1.2 kg)	12	g/10 min	ASTM D1238
Molding Shrinkage - Flow (0.125 in)	8.0E-3 to 0.010	in/in	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	350000	psi	ASTM D638
Tensile Strength (Yield)	3500	psi	ASTM D638
Tensile Strength (Break)	2500	psi	ASTM D638
Tensile Elongation (Break)	55	%	ASTM D638
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (0.125 in)	0.40	ft·lb/in	ASTM D256

Processing Information

Injection	Nominal Value	Unit
Drying Temperature	150	°F
Drying Time	2.0 to 3.0	hr
Rear Temperature	440 to 480	°F
Middle Temperature	450 to 490	°F
Front Temperature	460 to 500	°F
Nozzle Temperature	470 to 510	°F
Processing (Melt) Temp	450 to 510	°F
Mold Temperature	75 to 150	°F
Injection Rate	Slow-Moderate	
Back Pressure	25.0 to 75.0	psi
Screw Speed	Moderate	

Notes

¹ Typical properties: these are not to be construed as specifications.

