

InElec® PPCF25
Americhem - Polypropylene
General Information
Product Description

25% CARBON FIBER REINFORCED, ELECTRICALLY CONDUCTIVE POLYPROPYLENE

General

Material Status	• Commercial: Active		
Availability	• Africa & Middle East	• Europe	• North America
	• Asia Pacific	• Latin America	
Filler / Reinforcement	• Carbon Fiber, 25% Filler by Weight		
Features	• Electrically Conductive	• Good Dimensional Stability	• Permanent Antistatic
	• ESD Protection	• High Stiffness	
	• Filled	• High Strength	
Uses	• Closures	• Electrical/Electronic Applications	• Industrial Applications
	• Connectors	• Housings	• Industrial Parts
	• Consumer Applications	• HVAC Applications	
Forms	• Pellets		
Processing Method	• Injection Molding		

Properties ¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	1.02		ASTM D792
Molding Shrinkage - Flow (0.125 in)	3.0E-3 to 4.0E-3	in/in	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Break)	5600	psi	ASTM D638
Flexural Modulus	1.40E+6	psi	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	0.90	ft·lb/in	ASTM D256
Unnotched Izod Impact	2.3	ft·lb/in	ASTM D4812
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+2 to 1.0E+4	ohms	ASTM D257

Processing Information

Injection	Nominal Value	Unit
Drying Temperature	170	°F
Drying Time	2.0 to 4.0	hr
Processing (Melt) Temp	380 to 440	°F
Mold Temperature	100	°F
Back Pressure	50.0 to 100	psi
Screw Speed	40 to 70	rpm
Vent Depth	5.0E-4 to 1.0E-3	in

