

InLube® PPHGF30TF15
Americhem - Polypropylene Homopolymer
General Information
Product Description

30% GLASS FIBER REINFORCED, 15% PTFE LUBRICATED POLYPROPYLENE

General

Material Status	• Commercial: Active		
Availability	• Africa & Middle East • Asia Pacific	• Europe • Latin America	• North America
Filler / Reinforcement	• Glass Fiber, 30% Filler by Weight		
Additive	• PTFE Lubricant: 15%		
Features	• Chemical Resistant • Filled • Good Dimensional Stability	• Good Mold Release • High Stiffness • High Strength	• Low Friction • Lubricated • Wear Resistant
Uses	• Battery Cases • Closures • Connectors	• Consumer Applications • Electrical/Electronic Applications • Housings	• HVAC Applications • Industrial Applications • Industrial Parts
Forms	• Pellets		
Processing Method	• Injection Molding		

Properties ¹

	Nominal Value	Unit	Test Method
Physical			
Density / Specific Gravity	1.25		ASTM D792
Molding Shrinkage - Flow (0.125 in)	2.0E-3 to 5.0E-3	in/in	
Water Absorption (Equilibrium)	0.030	%	ASTM D570
Mechanical			
Tensile Strength (Break)	11900	psi	ASTM D638
Flexural Modulus	972000	psi	ASTM D790
Flexural Strength (Break)	18100	psi	ASTM D790
Impact			
Notched Izod Impact	1.3	ft·lb/in	ASTM D256
Unnotched Izod Impact	10 to 12	ft·lb/in	ASTM D4812
Thermal			
Deflection Temperature Under Load (264 psi, Unannealed)	280	°F	ASTM D648
Electrical			
Surface Resistivity	1.0E+17	ohms	ASTM D257

Processing Information

	Nominal Value	Unit
Injection		
Drying Temperature	170	°F
Drying Time	2.0 to 4.0	hr
Processing (Melt) Temp	380 to 440	°F
Mold Temperature	100 to 150	°F
Back Pressure	50.0 to 100	psi
Screw Speed	40 to 70	rpm

