

InStruc® PPGF50CC
Americhem - Polypropylene Homopolymer
General Information
Product Description

50% GLASS FIBER REINFORCED CHEMICALLY COUPLED POLYPROPYLENE

General

Material Status	• Commercial: Active		
Availability	• Africa & Middle East • Asia Pacific	• Europe • Latin America	• North America
Filler / Reinforcement	• Glass Fiber, 50% Filler by Weight		
Features	• Chemically Coupled • Filled	• Good Dimensional Stability • High Stiffness	• High Strength
Uses	• Battery Cases • Closures • Connectors	• Consumer Applications • Electrical/Electronic Applications • Housings	• HVAC Applications • Industrial Applications • Industrial Parts
Forms	• Pellets		
Processing Method	• Injection Molding		

Properties ¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	1.33		ASTM D792
Molding Shrinkage - Flow (0.125 in)	1.0E-3 to 3.0E-3	in/in	ASTM D955
Water Absorption (Equilibrium)	0.020	%	ASTM D570
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	1.50E+6	psi	ASTM D638
Tensile Strength	12000	psi	ASTM D638
Tensile Elongation (Yield)	3.0	%	ASTM D638
Flexural Modulus	1.30E+6	psi	ASTM D790
Flexural Strength	20500	psi	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	2.2	ft·lb/in	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (264 psi, Unannealed)	300	°F	ASTM D648

Processing Information

Injection	Nominal Value	Unit
Drying Temperature	170	°F
Drying Time	2.0 to 4.0	hr
Processing (Melt) Temp	440	°F
Mold Temperature	100	°F
Back Pressure	50.0 to 100	psi
Screw Speed	40 to 70	rpm

