

LATISTAT 52/7-02 MI/30

 LATI INDUSTRIA TERMOPLASTICI SPA - *Polypropylene Homopolymer*
General Information
Product Description

Dissipative product based on Polypropylene homopolymer (PPh). Mica filler. High dimensional stability. PFAS-free product.

General

Material Status	• Commercial: Active		
Availability	• Africa & Middle East	• Europe	• North America
	• Asia Pacific	• Latin America	
Filler / Reinforcement	• Mica		
Features	• Antistatic	• Homopolymer	• PFAS Free

Properties ¹

Physical	Nominal Value	Unit	Test Method
Density (73°F)	1.22	g/cm ³	ISO 1183
Molding Shrinkage ²			ISO 294-4
Across Flow : 0.0787 in	0.90 to 1.2	%	
Flow : 0.0787 in	0.90 to 1.2	%	
Water Absorption ³ (Saturation, 73°F)	0.050	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus (73°F)	566000	psi	ISO 527-1/1
Tensile Stress (Yield, 73°F)	3630	psi	ISO 527-2/5
Tensile Stress (Break, 73°F)	3630	psi	ISO 527-2/5
Tensile Strain (Yield, 73°F)	2.2	%	ISO 527-2/5
Tensile Strain (Break, 73°F)	3.3	%	ISO 527-2/5
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (73°F)	0.71	ft·lb/in ²	ISO 179/1eA
Charpy Unnotched Impact Strength (73°F)	7.1	ft·lb/in ²	ISO 179/1eU
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (66 psi, Unannealed)	266	°F	ISO 75-2/B
Deflection Temperature Under Load (264 psi, Unannealed)	194	°F	ISO 75-2/A
Vicat Softening Temperature	221	°F	ISO 306/B120
CLTE - Flow (86 to 212°F)	5.3E-5	in/in/°F	ISO 11359-2
CLTE - Transverse (86 to 212°F)	5.3E-5	in/in/°F	ISO 11359-2
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	9.0E+2	ohms	ASTM D257

Notes
¹ Typical properties: these are not to be construed as specifications.

² 60 MPa

³ in air
