

LATENE EP 4 UV MDT09-01 BL:7519F1

LATI INDUSTRIA TERMOPLASTICI SPA - *Polypropylene Copolymer*

General Information

Product Description

Compound based on Polypropylene copolymer (PPc). UV stabilised. Heat stabilised. Magnetic detectable filler. X-ray detectable grade. PFAS-free product.

General

Material Status	• Commercial: Active		
Availability	• Africa & Middle East • Asia Pacific	• Europe • Latin America	• North America
Filler / Reinforcement	• Filler		
Additive	• Heat Stabilizer	• UV Stabilizer	
Features	• Copolymer • Heat Stabilized • Magnetically Detectable	• Metal Detectable • PFAS Free • UV Resistant	• UV Stabilized

Properties ¹

Physical	Nominal Value	Unit	Test Method
Density (73°F)	1.38	g/cm ³	ISO 1183
Molding Shrinkage ²			ISO 294-4
Across Flow : 0.0787 in	1.3 to 1.6	%	
Flow : 0.0787 in	1.1 to 1.4	%	
Water Absorption ³ (Saturation, 73°F)	0.050	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus (73°F)	232000	psi	ISO 527-1/1
Tensile Stress (Yield, 73°F)	2180	psi	ISO 527-2/5
Tensile Stress (Break, 73°F)	No Break		ISO 527-2/5
Tensile Strain (Yield, 73°F)	4.5	%	ISO 527-2/5
Tensile Strain (Break, 73°F)	> 50	%	ISO 527-2/5
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (73°F)	7.1	ft·lb/in ²	ISO 179/1eA
Charpy Unnotched Impact Strength (73°F)	No Break		ISO 179/1eU
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (66 psi, Unannealed)	185	°F	ISO 75-2/B
Deflection Temperature Under Load (264 psi, Unannealed)	131	°F	ISO 75-2/A
Vicat Softening Temperature	176	°F	ISO 306/B120
CLTE - Flow (86 to 212°F)	5.6E-5	in/in/°F	ISO 11359-2
CLTE - Transverse (86 to 212°F)	5.6E-5	in/in/°F	ISO 11359-2
Thermal Conductivity			ASTM E1461
-- ⁴	1.4	Btu·in/hr/ft ² /°F	
-- ⁵	1.4	Btu·in/hr/ft ² /°F	
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+9	ohms	ASTM D257

Notes

¹ Typical properties: these are not to be construed as specifications.

² 60 MPa

³ in air

⁴ through plane

⁵ in plane

