

**OMNIPRO® CPP TF20 UV**
*Celanese Corporation - Polypropylene*
**General Information**
**Product Description**

Preliminary Datasheet. Data are based on limited testing. Values subject to change.

**General**

Material Status	• Commercial: Active
Availability	• Africa & Middle East      • Europe • Asia Pacific                      • Latin America                      • North America
Filler / Reinforcement	• Talc, 20% Filler by Weight
Part Marking Code (ISO 11469)	• >PP-T20<
Resin ID (ISO 1043)	• PP-T20

**Properties <sup>1</sup>**

Physical	Nominal Value	Unit	Test Method
Density	1.04	g/cm <sup>3</sup>	ISO 1183
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact Strength (73°F)	2.0	ft·lb/in <sup>2</sup>	ISO 180/1A
Flammability	Nominal Value	Unit	Test Method
Burning Rate <sup>2</sup> (0.0394 in)	3.1	in/min	ISO 3795
FMVSS Flammability	B		FMVSS 302

**Notes**
<sup>1</sup> Typical properties: these are not to be construed as specifications.

<sup>2</sup> FMVSS 302
