

## POLIMAXX K4520UB

IRPC Public Company Limited - *Polypropylene Random Copolymer*

### General Information

#### Product Description

K4520UB is a Polypropylene Random Copolymer (PP) with the characteristic of super high transparency and high melt flow ability. It is designed for injection molding processing.

#### Industry:

- Super Clear Food Containers
- Consumer Products
- Housewares

#### Product Feature:

- Super High Transparency
- High Gloss
- Good Processibility
- Improved color shade with Optical Brightener (OB Free)

#### Regulation Compliance:

- FDA US 21 CFR 177.1520
- Commission Regulation (EU) No. 10/2011
- RoHS Directive 2011/65/EU
- REACH Regulation (EC) No. 1907/2006
- Halal Certificate

#### General

Material Status	• Commercial: Active		
Availability	• Asia Pacific	• Europe	• North America
Features	• Good Processability	• High Flow	• Random Copolymer
	• High Clarity	• High Gloss	
Uses	• Consumer Applications	• Food Containers	• Household Goods
Agency Ratings	• EC 1907/2006 (REACH)	• EU No 10/2011	
	• EU 2011/65/EC	• FDA 21 CFR 177.1520	
RoHS Compliance	• RoHS Compliant		
Processing Method	• Injection Molding		

### Properties <sup>1</sup>

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity <sup>2</sup>	0.902		ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	25	g/10 min	ASTM D1238
Molding Shrinkage	1.2 to 1.7	%	Internal Method
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength <sup>3</sup> (Yield, 0.126 in)	4930	psi	ASTM D638
Tensile Elongation <sup>3</sup> (Yield, 0.126 in)	11	%	ASTM D638
Flexural Modulus - 1% Secant <sup>4</sup> (0.126 in)	186000	psi	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (73°F, 0.126 in)	0.84	ft-lb/in	ASTM D256
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale, 0.126 in)	97		ASTM D785
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (66 psi, Unannealed, 0.126 in)	185	°F	ASTM D648
Optical	Nominal Value	Unit	Test Method
Haze (39.37 mil)	4.00	%	ASTM D1003

### Processing Information



<b>Injection</b>	<b>Nominal Value</b>	<b>Unit</b>
Rear Temperature	374 to 464	°F
Middle Temperature	374 to 464	°F
Front Temperature	374 to 464	°F
Mold Temperature	122 to 176	°F
Injection Rate		Slow-Moderate

#### Notes

<sup>1</sup> Typical properties: these are not to be construed as specifications.

<sup>2</sup> 23°C

<sup>3</sup> 2.0 in/min

<sup>4</sup> 0.051 in/min

