

## POLIMAXX K4527ET

IRPC Public Company Limited - Polypropylene Random Copolymer

### General Information

#### Product Description

K4527ET is a Medical Grade Polypropylene Random Copolymer (RCPP) with the characteristic of high transparency and high melt flow ability. It is designed for injection molding processing.

#### Industry:

- Medical Devices
- Syringes
- Labwares

#### Product Feature:

- Medical Grade
- High Transparency
- High Gloss
- Natural Color (OB Free)
- Ethylene Oxide Sterilization

#### Regulation Compliance:

- FDA US 21 CFR 177.1520
- Commission Regulation (EU) No. 10/2011
- RoHS Directive 2011/65/EU
- REACH Regulation (EC) No.1907/2006
- Halal Certificate
- USP Class VI
- EP 3.1.6

#### General

Material Status	• Commercial: Active		
Availability	• Asia Pacific	• Europe	• North America
Features	• Ethylene Oxide Sterilizable	• High Flow	• Odorless
	• High Clarity	• High Gloss	• Random Copolymer
Uses	• Labware	• Medical Devices	• Medical/Healthcare Applications
Agency Ratings	• EC 1907/2006 (REACH)	• EU 2011/65/EC	• FDA 21 CFR 177.1520
	• EP Monograph 3.1.6	• EU No 10/2011	• USP Class IV
RoHS Compliance	• RoHS Compliant		
Processing Method	• Injection Molding		

### Properties <sup>1</sup>

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity <sup>2</sup>	0.902		ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	27	g/10 min	ASTM D1238
Molding Shrinkage	1.2 to 1.7	%	Internal Method
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength <sup>3</sup> (Yield, 0.126 in)	4350	psi	ASTM D638
Tensile Elongation <sup>3</sup> (Yield, 0.126 in)	13	%	ASTM D638
Flexural Modulus - 1% Secant <sup>4</sup> (0.126 in)	167000	psi	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (73°F, 0.126 in)	0.94	ft-lb/in	ASTM D256
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale, 0.126 in)	91		ASTM D785
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (66 psi, Unannealed, 0.126 in)	176	°F	ASTM D648



Optical	Nominal Value	Unit	Test Method
Haze (39.37 mil)	8.00	%	ASTM D1003

### Processing Information

Injection	Nominal Value	Unit
Rear Temperature	410 to 464	°F
Middle Temperature	410 to 464	°F
Front Temperature	410 to 464	°F
Mold Temperature	122 to 176	°F
Injection Rate	Slow-Moderate	

### Notes

<sup>1</sup> Typical properties: these are not to be construed as specifications.

<sup>2</sup> 23°C

<sup>3</sup> 2.0 in/min

<sup>4</sup> 0.051 in/min

