

TAIRIPRO® K4535

 Formosa Chemicals & Fibre Corporation - *Polypropylene Random Copolymer*
General Information
Product Description

Injection Molding

Features: High fluidity, High Clarity, Anti-static, Good resistance to chemical

General

Material Status	• Commercial: Active		
Availability	• Asia Pacific	• Europe	• North America
Features	• Antistatic	• High Clarity	• Random Copolymer
	• Chemical Resistant	• High Flow	
Uses	• Film		
Agency Ratings	• EC 1907/2006 (REACH)	• FDA 21 CFR 177.1520(c) 3.1a	
RoHS Compliance	• RoHS Compliant		
UL File Number	• E162823		

Properties ¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity ²	0.902		ASTM D792
Density (73°F)	0.900	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	35	g/10 min	ASTM D1238
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	35	g/10 min	ISO 1133
Molding Shrinkage (73°F)	1.5 to 2.0	%	Internal Method
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength ³ (73°F)	4410	psi	ASTM D638
Tensile Stress (73°F)	4350	psi	ISO 527-2/50
Tensile Elongation ³ (Break, 73°F)	> 200	%	ASTM D638
Tensile Strain (Break, 73°F)	> 200	%	ISO 527-2/50
Flexural Modulus (73°F)	164000	psi	ASTM D790
Flexural Modulus (73°F)	164000	psi	ISO 178
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact			ASTM D256
73°F, 0.125 in	0.92	ft·lb/in	
73°F, 0.157 in	0.92	ft·lb/in	
Notched Izod Impact Strength			ISO 180
73°F, 0.125 in	23	ft·lb/in ²	
73°F, 0.157 in	23	ft·lb/in ²	
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale, 73°F)	95		ASTM D785
Rockwell Hardness (R-Scale, 73°F)	95		ISO 2039-2
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load ⁴ (66 psi, Unannealed, 0.250 in)	203	°F	ASTM D648
Deflection Temperature Under Load ⁴ (66 psi, Unannealed, 0.250 in)	203	°F	ISO 75-2/B
Flammability	Nominal Value	Unit	Test Method
Flame Rating (0.06 in, All Color)	HB		UL 94

Processing Information

Injection	Nominal Value	Unit
Mold Temperature	86 to 122	°F



Injection Pressure	569 to 1280 psi
Notes	
¹ Typical properties: these are not to be construed as specifications.	
² 23°C	
³ 2.0 in/min	
⁴ 120°C/h	

