

**TAIRIPRO® K1525**

 Formosa Chemicals & Fibre Corporation - *Polypropylene Homopolymer*

## General Information

**Product Description**

Injection Molding

Features: High fluidity, High stiffness, Good luster, Good transparency

**General**

Material Status	• Commercial: Active		
Availability	• Asia Pacific	• Europe	• North America
Features	• Good Clarity	• High Stiffness	
	• High Flow	• Homopolymer	
Agency Ratings	• EC 1907/2006 (REACH)	• FDA 21 CFR 177.1520	
RoHS Compliance	• RoHS Compliant		
UL File Number	• E162823		
Appearance	• Clear/Transparent		
Processing Method	• Injection Molding		

 Properties <sup>1</sup>

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity <sup>2</sup>	0.902		ASTM D792
Density (73°F)	0.900	g/cm <sup>3</sup>	ISO 1183
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	25	g/10 min	ASTM D1238
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	25	g/10 min	ISO 1133
Molding Shrinkage (73°F)	1.4 to 1.8	%	Internal Method
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength <sup>3</sup> (73°F)	5120	psi	ASTM D638
Tensile Stress (73°F)	5080	psi	ISO 527-2/50
Tensile Elongation <sup>3</sup> (Break, 73°F)	> 50	%	ASTM D638
Tensile Strain (Break, 73°F)	> 50	%	ISO 527-2/50
Flexural Modulus (73°F)	256000	psi	ASTM D790
Flexural Modulus (73°F)	256000	psi	ISO 178
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact			ASTM D256
73°F, 0.125 in	0.48	ft·lb/in	
73°F, 0.157 in	0.48	ft·lb/in	
Notched Izod Impact Strength			ISO 180
73°F, 0.125 in	12	ft·lb/in <sup>2</sup>	
73°F, 0.157 in	12	ft·lb/in <sup>2</sup>	
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale, 73°F)	108		ASTM D785
Rockwell Hardness (R-Scale, 73°F)	108		ISO 2039-2
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load <sup>4</sup> (66 psi, Unannealed, 0.250 in)	257	°F	ASTM D648
Deflection Temperature Under Load <sup>4</sup> (66 psi, Unannealed, 0.250 in)	257	°F	ISO 75-2/B
Flammability	Nominal Value	Unit	Test Method
Flame Rating			UL 94
0.06 in, All Color		HB	
0.06 to 0.12 in		HB	
0.12 in, All Color		HB	



## Processing Information

Injection	Nominal Value	Unit
Mold Temperature	86 to 122	°F
Injection Pressure	1140 to 1710	psi

### Notes

<sup>1</sup> Typical properties: these are not to be construed as specifications.

<sup>2</sup> 23°C

<sup>3</sup> 2.0 in/min

<sup>4</sup> 120°C/h

