

TAIRIPRO® F4006

Formosa Chemicals & Fibre Corporation - Polypropylene Random Copolymer

General Information

Product Description

Film

Features: Good Transparency

General

Material Status	• Commercial: Active
Availability	• Asia Pacific • Europe • North America
Features	• Good Clarity • Random Copolymer
Uses	• Film
Agency Ratings	• EC 1907/2006 (REACH) • FDA 21 CFR 177.1520(c) 3.1a
RoHS Compliance	• RoHS Compliant
UL File Number	• E162823
Appearance	• Clear/Transparent
Processing Method	• Film Extrusion

 Properties ¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity ²	0.902		ASTM D792
Density (73°F)	0.900	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	7.5	g/10 min	ASTM D1238
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	7.5	g/10 min	ISO 1133
Molding Shrinkage (73°F)	1.5 to 2.0	%	Internal Method
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength ³ (73°F)	3700	psi	ASTM D638
Tensile Stress (73°F)	3630	psi	ISO 527-2/50
Tensile Elongation ³ (Break, 73°F)	> 200	%	ASTM D638
Tensile Strain (Break, 73°F)	> 200	%	ISO 527-2/50
Flexural Modulus (73°F)	121000	psi	ASTM D790A
Flexural Modulus (73°F)	121000	psi	ISO 178
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact			ASTM D256
73°F, 0.125 in	1.2	ft·lb/in	
73°F, 0.157 in	1.2	ft·lb/in	
Notched Izod Impact Strength			ISO 180
73°F, 0.125 in	30	ft·lb/in ²	
73°F, 0.157 in	30	ft·lb/in ²	
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale, 73°F)	85		ASTM D785
Rockwell Hardness (R-Scale, 73°F)	85		ISO 2039-2
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load ⁴ (66 psi, Unannealed, 0.250 in)	185	°F	ASTM D648
Deflection Temperature Under Load ⁴ (66 psi, Unannealed, 0.250 in)	185	°F	ISO 75-2/B

