

Thermylene® P10-30FG-0604

 Asahi Kasei Plastics North America Inc. - *Polypropylene*
General Information
Product Description

This is a high-performance, high-flow, glass reinforced, heat and metal stabilized polypropylene compound designed for structural applications. It is suited for light-weighting by replacement of high density engineered materials.

General

Material Status	• Commercial: Active
Availability	• Africa & Middle East • Europe • North America • Asia Pacific • Latin America
Filler / Reinforcement	• Glass Fiber, 30% Filler by Weight
Additive	• Heat Stabilizer
Features	• Heat Stabilized • High Flow

Properties ¹

Physical	Nominal Value	Unit	Test Method
Density	1.13	g/cm ³	ISO 1183/A
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	13	g/10 min	ISO 1133
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress	15500	psi	ISO 527-2
Flexural Modulus	957000	psi	ISO 178
Flexural Stress	23200	psi	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (73°F)	4.8	ft·lb/in ²	ISO 179
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (264 psi, Unannealed)	309	°F	ISO 75-2/A

