

Thermylene® P6-15FG-1735

 Asahi Kasei Plastics North America Inc. - *Polypropylene*
General Information
Product Description

This is a glass reinforced, heat-stabilized, polypropylene compound that has been designed for good impact performance.

General

Material Status	• Commercial: Active
Availability	• Africa & Middle East • Europe • North America • Asia Pacific • Latin America
Filler / Reinforcement	• Glass Fiber, 15% Filler by Weight
Additive	• Heat Stabilizer
Features	• Good Impact Resistance • Heat Stabilized

Properties ¹

Physical	Nominal Value	Unit	Test Method
Density	1.01	g/cm ³	ISO 1183/A
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	7.5	g/10 min	ISO 1133
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress	6960	psi	ISO 527-2
Flexural Modulus	442000	psi	ISO 178
Flexural Stress	11000	psi	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (73°F)	5.9	ft·lb/in ²	ISO 179
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (264 psi, Unannealed)	257	°F	ISO 75-2/A

Notes
¹ Typical properties: these are not to be construed as specifications.
