

**Thermylene® P6-20FG-0753**

 Asahi Kasei Plastics North America Inc. - *Polypropylene*
**General Information**
**Product Description**

This is a glass reinforced, heat-stabilized, polypropylene compound that has been designed for applications requiring good ductility.

**General**

Material Status	• Commercial: Active
Availability	• Africa & Middle East • Europe • North America • Asia Pacific • Latin America
Filler / Reinforcement	• Glass Fiber, 20% Filler by Weight
Additive	• Heat Stabilizer
Features	• Ductile • Heat Stabilized

**Properties <sup>1</sup>**

<b>Physical</b>	<b>Nominal Value</b>	<b>Unit</b>	<b>Test Method</b>
Density	1.04	g/cm <sup>3</sup>	ISO 1183/A
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	12	g/10 min	ISO 1133
<b>Mechanical</b>	<b>Nominal Value</b>	<b>Unit</b>	<b>Test Method</b>
Tensile Stress	9430	psi	ISO 527-2
Flexural Modulus	595000	psi	ISO 178
Flexural Stress	14600	psi	ISO 178
<b>Impact</b>	<b>Nominal Value</b>	<b>Unit</b>	<b>Test Method</b>
Charpy Notched Impact Strength (73°F)	4.0	ft·lb/in <sup>2</sup>	ISO 179
<b>Thermal</b>	<b>Nominal Value</b>	<b>Unit</b>	<b>Test Method</b>
Deflection Temperature Under Load (264 psi, Unannealed)	284	°F	ISO 75-2/A

**Notes**

<sup>1</sup> Typical properties: these are not to be construed as specifications.

