

Thermylene® P6-25FG-1684

 Asahi Kasei Plastics North America Inc. - *Polypropylene*
General Information
Product Description

This polypropylene compound is UV stabilized and is ideal for water handling applications where exposure to weathering is likely.

General

Material Status	• Commercial: Active
Availability	• Africa & Middle East • Europe • Asia Pacific • Latin America • North America
Filler / Reinforcement	• Glass Fiber, 25% Filler by Weight
Additive	• UV Stabilizer
Features	• UV Stabilized

Properties ¹

Physical	Nominal Value	Unit	Test Method
Density	1.09	g/cm ³	ISO 1183/A
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	3.0	g/10 min	ISO 1133
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress	8990	psi	ISO 527-2
Flexural Modulus	653000	psi	ISO 178
Flexural Stress	14400	psi	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (73°F)	2.9	ft·lb/in ²	ISO 179
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (264 psi, Unannealed)	271	°F	ISO 75-2/A

Notes
¹ Typical properties: these are not to be construed as specifications.
