

Thermylene® P8-20FG-0876

 Asahi Kasei Plastics North America Inc. - *Polypropylene*
General Information
Product Description

This superior performance compound has been optimized with a UV stabilization package.

General

Material Status	• Commercial: Active
Availability	• Africa & Middle East • Europe • North America • Asia Pacific • Latin America
Filler / Reinforcement	• Glass Fiber, 20% Filler by Weight
Additive	• UV Stabilizer
Features	• UV Stabilized

Properties ¹

Physical	Nominal Value	Unit	Test Method
Density	1.05	g/cm ³	ISO 1183/A
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	8.0	g/10 min	ISO 1133
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress	9570	psi	ISO 527-2
Flexural Modulus	609000	psi	ISO 178
Flexural Stress	14900	psi	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (73°F)	3.3	ft·lb/in ²	ISO 179
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (264 psi, Unannealed)	284	°F	ISO 75-2/A

