

**Thermylene® P6-30FG-0687**

 Asahi Kasei Plastics North America Inc. - *Polypropylene*
**General Information**
**Product Description**

This general purpose polypropylene compound has been heat stabilized for high temperature underhood applications.

**General**

Material Status	• Commercial: Active		
Availability	• Africa & Middle East	• Europe	• North America
	• Asia Pacific	• Latin America	
Filler / Reinforcement	• Glass Fiber, 30% Filler by Weight		
Additive	• Heat Stabilizer		
Features	• General Purpose	• Heat Stabilized	
Uses	• Automotive Under the Hood	• General Purpose	
Automotive Specifications	• FORD WSS-M4D936-A1		

**Properties <sup>1</sup>**

<b>Physical</b>	<b>Nominal Value</b>	<b>Unit</b>	<b>Test Method</b>
Density	1.13	g/cm <sup>3</sup>	ISO 1183/A
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	12	g/10 min	ISO 1133
<b>Mechanical</b>	<b>Nominal Value</b>	<b>Unit</b>	<b>Test Method</b>
Tensile Stress	12300	psi	ISO 527-2
Flexural Modulus	856000	psi	ISO 178
Flexural Stress	19000	psi	ISO 178
<b>Impact</b>	<b>Nominal Value</b>	<b>Unit</b>	<b>Test Method</b>
Charpy Notched Impact Strength (73°F)	4.3	ft·lb/in <sup>2</sup>	ISO 179
<b>Thermal</b>	<b>Nominal Value</b>	<b>Unit</b>	<b>Test Method</b>
Deflection Temperature Under Load (264 psi, Unannealed)	295	°F	ISO 75-2/A

**Notes**
<sup>1</sup> Typical properties: these are not to be construed as specifications.
