

Thermylene® P6-30FG-0688

 Asahi Kasei Plastics North America Inc. - *Polypropylene*
General Information
Product Description

This general purpose polypropylene compound has been designed for applications requiring good UV resistance.

General

Material Status	• Commercial: Active
Availability	• Africa & Middle East • Europe • North America • Asia Pacific • Latin America
Filler / Reinforcement	• Glass Fiber, 30% Filler by Weight
Features	• General Purpose • UV Resistant
Uses	• General Purpose

Properties ¹

Physical	Nominal Value	Unit	Test Method
Density	1.13	g/cm ³	ISO 1183/A
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	6.0	g/10 min	ISO 1133
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress	12900	psi	ISO 527-2
Flexural Modulus	885000	psi	ISO 178
Flexural Stress	19900	psi	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (73°F)	4.8	ft·lb/in ²	ISO 179
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (264 psi, Unannealed)	295	°F	ISO 75-2/A

Notes
¹ Typical properties: these are not to be construed as specifications.
