

**XYRON™ 240W**

Asahi Kasei Corporation - Polyphenylene Ether + PS

**General Information**
**Product Description**

 Modified PPE  
 Unreinforced Flame retardant V-2  
 Easy flow

**General**

Material Status	• Commercial: Active
Availability	• Africa & Middle East • Europe • Asia Pacific • North America
Additive	• Flame Retardant
Features	• Flame Retardant • Halogen Free
Processing Method	• Injection Molding
Part Marking Code (ISO 11469)	• >PPE+PS-FR(40)<

**Properties <sup>1</sup>**

Physical	Nominal Value	Unit	Test Method
Density	1.07	g/cm <sup>3</sup>	ISO 1183
Molding Shrinkage <sup>2</sup> (0.0787 in)	0.50 to 0.70	%	Internal Method
Water Absorption (24 hr, 73°F)	0.10	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress (Yield, 73°F)	6090	psi	ISO 527
Nominal Tensile Strain at Break (73°F)	28	%	ISO 527
Flexural Modulus (73°F)	334000	psi	ISO 178
Flexural Stress (73°F)	10600	psi	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength <sup>3</sup> (73°F)	7.6	ft-lb/in <sup>2</sup>	ISO 179
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (264 psi, Unannealed)	190	°F	ISO 75-2/A
CLTE - Flow (-22 to 149°F)	3.9E-5	in/in/°F	ISO 11359-2
CLTE - Transverse (-22 to 149°F)	4.4E-5	in/in/°F	ISO 11359-2
Heat Deflection Temperature - (1.8 MPa, Unannealed)	194	°F	ASTM D648
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+16	ohms	IEC 60093
Volume Resistivity (73°F)	1.0E+16	ohms·cm	IEC 60093
Dielectric Constant			IEC 60250
100 Hz	2.90		
1 MHz	2.90		
Dissipation Factor			IEC 60250
100 Hz	3.0E-3		
1 MHz	4.0E-3		
Flammability	Nominal Value	Unit	Test Method
Flame Rating (0.06 in)	V-2		UL 94

**Processing Information**

Injection	Nominal Value	Unit
Drying Temperature - Dry Air Dryer	176 to 194	°F
Drying Time - Dry Air Dryer	2.0 to 4.0	hr
Processing (Melt) Temp	428 to 518	°F
Mold Temperature	104 to 158	°F



---

## Notes

---

<sup>1</sup> Typical properties: these are not to be construed as specifications.

---

<sup>2</sup> 150x150x2 mm

---

<sup>3</sup> 4 mm

---

