

LATIOHM 90/13-09 PD01 G/10

 LATI INDUSTRIA TERMOPLASTICI SPA - *Polyphenylene Ether + PS*
General Information
Product Description

Semiconductive/dissipative product based on Modified Polyphenylene Oxide (PPE/PS). Glass fibres. PFAS-free product.

General

Material Status	• Commercial: Active		
Availability	• Africa & Middle East	• Europe	• North America
	• Asia Pacific	• Latin America	
Filler / Reinforcement	• Glass Fiber		
Features	• Antistatic	• Electrically Conductive	• PFAS Free

Properties ¹

Physical	Nominal Value	Unit	Test Method
Density (73°F)	1.18	g/cm ³	ISO 1183
Molding Shrinkage ²			ISO 294-4
Across Flow : 0.0787 in	0.50 to 0.80	%	
Flow : 0.0787 in	0.25 to 0.50	%	
Water Absorption ³ (Saturation, 73°F)	0.040	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus (73°F)	1.16E+6	psi	ISO 527-1/1
Tensile Stress (Break, 73°F)	11600	psi	ISO 527-2/5
Tensile Strain (Break, 73°F)	1.2	%	ISO 527-2/5
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (73°F)	1.7	ft·lb/in ²	ISO 179/1eA
Charpy Unnotched Impact Strength (73°F)	7.1	ft·lb/in ²	ISO 179/1eU
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (66 psi, Unannealed)	266	°F	ISO 75-2/B
Deflection Temperature Under Load (264 psi, Unannealed)	248	°F	ISO 75-2/A
Vicat Softening Temperature	275	°F	ISO 306/B120
CLTE - Flow (86 to 212°F)	1.1E-5	in/in/°F	ISO 11359-2
CLTE - Transverse (86 to 212°F)	3.1E-5	in/in/°F	ISO 11359-2
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	50	ohms	ASTM D257
Volume Resistivity	80	ohms·cm	ASTM D257

Notes
¹ Typical properties: these are not to be construed as specifications.

² 60 MPa

³ in air
